










T05G190402 POLISHED 90×1800/35.4"×70.8" T09G240402 POLISHED 90×1800/35.4"×70.8"

Description:

The aesthetics of architecture lie in the details: the beauty of a building's geometry and the refinement of a tile's patterns. Big Slab Baffin is born to reproduce all the details of understated elegance with a modern edge, adding a touch of accessible luxury to any spaces.

Made To Measure





			-	
	1.0	100		1
		Т	1	l
			100	
	100			1
100	100	10.0	1.00	1
				1
C+0	00	ord	- d	ι

Mini-grid

Checker board

159







Marbl
Marble
Cement
Stone
Textile
Mood







Staggered brickwork

Staggered brickwork



Staggered brickwork





Technical **Standards**

Tiles can be cut following the pattern or against the pattern. Special cuts outside this list can be provided under request.

SPECIAL PIECES

SLOT






Longitudinal

Square slot

SKIRTING





Bull-nose cut

STEPS Anti-slip surface







Bull-nose cut


Bevel cut






EDGES

Bull-nose cut





Bevel joint

MADE TO MEASURE

												Γ
												L
												Г
												L
												ſ
												L
												ſ
												L
												ſ
L												L
												ſ
												L
Ν	۱ir	٦İ	-C	٦r	ic							(
			- C	7° '								

[
_	_			_		
St	ag	90	je	re	d	

brickwork

Diamond

Checker board





PLACEMENT GUIDE

1. Before box opening, please verify product specification/ dimension, color, etc; make sure product of the same model is put in the same area instead of blending product of different types (unless a special decorative effect is pursued on purpose).

2. Before placement, dress the wall or floor well; determine brick arrangement according to placement type; in case of directional pattern, the product shall be applied as per the marked direction to reach the optimal decorative effect.

3. During pre-placement, pull two mutually vertical lines in the dressed ground and check leveling with the spirit meter; the wall vertically is checked by the plummet.

4. The ceramic sheet is recommended to be used together with 225#cement; the ceramic tile is recommended to be used together with 325#cement or glue; before placement, the ceramic sheet shall be fully soaked instead of ceramic tile.

5. Mark line according to tile dimension and pay attention to reserve mortar joint.



Honeycomb





6. During placement, tightly seal the joint by glue; upon request by customers, proper color additive can be used to fill in the joint.

7. During placement in main wall corner, proper amount of glue is applied to reach 1 cm thickness; put one tile in the glue; slightly knock it with a wooden hammer to ensure the tile surface, edge and the pulled line in parallel or vertical position.

8. During placement of wall tile, slightly knock on the tile a good many times till it is tightly fastened.

9.After placement in 1 hour, clean cement or other dirt in the tile surface timely till thorough cleanliness of tile surface.

10. After placement in 12 hours, make inspection by knocking on the tile surface. In case of hollow sound, rework is required.

11. Don't walk on or sweep the tile till 24 hours after placement. Thoroughly clean the tile by fresh water mixed with detergent. The shining floor and wall will be presented in front of you.

Technical **Standards**

GLAZED PORCELAIN

PROPERTIES	UNIT		ISO STANDARD REQUIREMENT						
			The deviation of the average size of each tile from the work size	±0.5	-0.02- +0.0				
Size & Deviation	%	SIDE	The deviation of the average size for each tile from the work size of the 10 test speciments	±0.4	-0.01 - +0.0				
			Thickness ±5						
Straighteness of sides	%		±0.2						
Rectangularity	%		±0.5						
			Center curvature	±0.4	-0.02 - +0.0				
Surface flatness	mm		±0.4	-0.02 - +0.0					
			Side curvature ±0.4						
Surface quality	-		A minimum of 95% of the tiles shall be free from chip, crack speek and visible defects that would impair the appearence of major area of						
	07		Average: E ≤0.5						
Water absorption	%		Single piece:E≤0.6						
Breaking Strength	Ν	When	When the thickness ≥7,5mm, the mean value shall not be less than 1300						
Anti-slip	R		9						
Resistance to household chemical reagent & swimmimg	-		No less than Class UB after test						
Resistance to low concentration acid or alkali	-		Report the result after test						
Stain resistance	-		No less than Class 3 after test						
Certificate of static friction	_		Report the result after text						
	_		Report the result after test Dry						
Lead release Cadmium	mg/dm	ng/dm Report the result after test							
release	mg/L								

UNGLAZED PORCELAIN

PROPERTIES	UNIT		ISO STANDARD REQUIREMENT							
	%		The deviation of the average size of each tile from the work size	±0.5	-0.01- +0.02					
Size & Deviation		SIDE	The deviation of the average size for each tile from the work size of the 10 test speciments	±0.4	-0.02 - +0.01					
			Thickness	±5	-0.9 - +0.9					
Straighteness of sides	%		±0.2							
Deetengularity	22.22		Length difference of opposite sides ≤2.0		0.5					
Rectangularity	mm		Length difference of diagonal lines ≤2.0		0.3					
Curfere e Aetre ere			Upward warpage	≤2.0	0.3					
Surface flatness	mm		0.3							
Surface quality	-		Downward warpage ≤2.0 A minimum of 95% of the tiles shall be free from chip, crack speek and visible defects that would impair the appearence of major area of tiles							
Westerneleserretien	%		0.06%							
Water absorption				0.4%-0.08%						
Breaking strength	Ν		2491							
Modulus of Rupture	MPA		Average: ≥35 Single piece: ≥32							
Abrasion resistance	mm		Abrassion CBM ≤175							
Glossiness	-		≥55							
Resistance to household chemical reagent & swimmimg pool alkali	-		No less than Class UB after test							
Thermal shock resistance	-		Report the result after test		No crack					
Resistance to low concentration acid or alkali	-		Report the result after test		Class ULA					
Stain resistance	-		No less than Class 3 after test		Class 5					
Coefficient of linear expansion			Report the result after test		7.1×10 ⁻⁶					
Moisture expansion (mm/m)			Report the result after test		< 0.01					
Shock recovery coefficient	-		Report the result after test		0.83					
			Wet							
Certificate of static friction	-		Report the result after test Dry							