

EUROLUB SEILFETT TW

Category:	Spray oils and penetrating oils		
Product Features:	Seilfett TW is a temporary corrosion protection agent for metallic surfaces (small metal parts), as well as for vehicle cavity preservation.		
Storage:	In the closed original container at max. + 30 ° C. When stored at <+ 10 ° C, warm to 30 ° C before use and homogenize.		
Application:	<p>Seilfett TW contains a solvent. After evaporation of the solvent, a thin, non-slip film is formed on the surfaces. Low viscosity for easy processing or application. When properly used, the preserved surfaces are reliably protected against corrosion.</p> <p>Seilfett TW can be applied at normal temperature by spraying, dipping or brushing on cleaned metal surfaces.</p> <p>A favorable processing temperature for surface application is approx. 25 to 35 ° C. The formation of the preservative film takes place with sufficient air movement after 2 to 8 hours.</p> <p>The temperature of the surface of the workpiece to be treated must be at least 3 ° C above the dew point.</p>		
Delivery:	Art.-Nr. 720600	12 x 600 ml	Aerosoldose
	Art.-Nr. 720001	12 x 1 Liter	tin can
	Art.-Nr.720005	5 Liter	tin can
	Art.-Nr. 720020	20 Liter	plastic can
	Art.-Nr. 720060	60 Liter	hobbock
	Art.-Nr. 720208	208 Liter	drum

Technical Data:

Density (15°C):	0,86 g/ml
Viscosity (flow time at 25°C, #4)	>40 s
Dropping Point (Ubbelohde), (solids) DIN 51801, Teil 2	> 80 °C
Solids content:	50 %
Aromatic content in solvent:	< 0,1 %
Layer thickness:	80 - 100 µm
Order quantity:	285 g/m ²
Labeling:	See current safety data sheet
General Notes:	none

The data provided are subject to change. Operating rules of the manufacturer. Characteristics are typical of current production data are subject to change. This should describe the products and should not therefore intended to assure certain properties. Obligation can not be derived.