



ARBOR
WOOD CO.

SLIP RESISTANCE DATA SHEET - ASH

(ANSI A137.1 / A326.3)

Arbor Wood Co.

1025 LONDON ROAD
DULUTH, MN
55802

1-855-414-2727

arborwoodco.com





**ARBOR
WOOD CO.**

TEST DATE:	4/23/2024	REPORT DATE:	4/24/2024
LOCATION:	LAB	CLIENT:	ARBOR WOOD CO.
FLOOR TYPE:	WOOD PLANK 5.5" X 16"	SURFACE REF:	ASH 1
DEVICE USED:	BOT 3000E	BOT SERIAL NO:	809
CALIBRATION DATE:	2/15/2024	VERIFICATION:	COMPLETED 04/23/24
SENSOR TYPES:	SBR	DISTANCE:	6 INCHES

TECHNICIAN: DC

TEST RESULTS							
TEST DATA	TEMP (F°)	HUMIDITY (%RH)	1	2	3	4	AVERAGE DCOF
TEST 1	70°	56	0.58	0.51	0.55	0.57	0.55
TEST 2	70°	56	0.55	0.47	0.56	0.49	0.52
TEST 3	70°	56	0.52	0.51	0.51	0.49	0.51
Final DCOF Rating							0.53

Specification: American National Standard A1371 / A326.3 -Test Method for Measuring Dynamic Coefficient of Friction (DCOF) of Hard-Surface Flooring Materials

TEST PROCEDURE DCOF

Test was conducted using a BOT-3000E digital tribometer with the SBR rubber sensor. Surface was cleaned with diluted Renovator #120, dried and then wetted with a surfactant solution of 0.05% Sodium Lauryl Sulfate in distilled water.

The ANSI standard, Section 3.1 states: "Unless otherwise specified, hard surface flooring materials suitable for level interior spaces expected to be walked upon when wet with water shall have a wet DCOF of 0.42 or greater when tested using SBR sensor material and SLS solution as per this standard. However, hard surface flooring materials with a DCOF of 0.42 or greater are not necessarily suitable for all projects. The specifier shall determine materials appropriate for specific project conditions, considering by way of example, but not in limitation, type of use, traffic, expected contaminants, expected maintenance, expected wear, and manufacturers' guidelines and recommendations."

This testing was completed by SlipDoctors to provide a snapshot of current conditions at the above location at the time of testing and is not intended or guaranteed to represent conditions at the time of installation or any later date. Re-testing is recommended after installation. This Test Report may not be reproduced without the written approval of SlipDoctors

TEST PERFORMED BY THE SLIP DOCTORS
 2101 Midway Road, Suite 350 | Carrollton, TX 75006 U.S.A.
 TEL: +972-999-9998 FAX: +214-666-3225 www.slipdoctors.com