



Fleece-back TPO 80 mil Membrane

APPLICABLE STANDARDS

UL approved for use in the construction of Class A, B, or C roofs; FM Approved, Miami-Dade County Approved, Florida Building Code Approved, CRRC Listed, Title 24 Compliant*, ENERGY STAR® Qualified**, ASTM D6878.

Physical Properties	ASTM Test Method	ASTM D6878 Minimum	EverGuard® Typical Test Data
1. Certain data is provided in MD (machine direction) x CMD (cross machine direction) format.			
2. Data is based upon typical product performance, and is subject to normal manufacturing tolerance and variance.			
Nominal Thickness	ASTM D751	0.039" (min.) (0.99 mm)	0.080" (2.03 mm)
Breaking Strength	ASTM D751 Grab Method	220 lbf/in. (38.5 kn/m)	440 lbf x 390 lbf (656 x 581 kg/m)
Factory Seam Strength	ASTM D751	66 lbf (98.34 kg/m)	155 lbf (231kg/m) (membrane failure)
Elongation at Break	ASTM D751	15%	30%
Heat Aging	ASTM D573	90% Retention of Breaking Strength and Elongation at Break	100%
Tear Strength	ASTM D751 8" x 8" (203 x 203 mm) Sample	55 lbf (81.95 kg/m)	100 lbf x 180 lbf (149 x 268 kg/m)
Puncture Resistance	FTM 101C Method 2031	Not Established	>380 lbs. (172 kg)
Cold Brittleness	ASTM D2137	-40°C	-40°C
Permeance	ASTM E96	Not Established	0.08 Perms
Dimensional Change	ASTM D1204 @158°F (70°C), 6 hrs.	+/- 1%	0.4%
Water Absorption	ASTM D471 @158°F (70°C), 1 week	+/- 3.0% max.	0.7%
Hydrostatic Resistance	ASTM D751 Method D	Not Established	430 psi
Ozone Resistance	ASTM D1149	No visible deterioration @ 7 x magnification	No visible deterioration @ 7 x magnification
Reflectivity (white) Initial/Aged	ASTM C1549	N/A	0.76/0.68
Emissivity (white) Initial/Aged	ASTM C1371	N/A	0.90/0.83
Weather Resistance	ASTM G155/D6878	10,080 KJ/(m ² . nm) at 340 nm	>25,000 KJ/(m ² . nm) at 340 nm
Heat Aging	ASTM D573	240°F (115°C) for 32 weeks	60 weeks
Thickness Above Scrim	ASTM D7635	Min 30% of Total Thickness	31.4 mil (Nominal)
Guarantee			
Up to 30 years			

*ENERGY STAR® only valid in the USA *White Membrane Only
 In view of innovation, the specifications are subject to change without any prior notice and in the event of such changes, BMI shall ensure that the new specifications are equivalent if not better.

PRODUCT INFORMATION

Roll Size Note: Product sizes, dimensions, and widths are nominal values and are subject to normal manufacturing/packaging tolerance and variation.

Colors	Full Size Roll	Full Roll Weight	Half Roll Size	Half Roll Weight
White	10' x 50'	238 lbs. (108 kg)	5' x 50'	112 lbs. (51 kg)
Tan	(3.05 x 15.24 m)		(1.52 x 15.24 m)	
Gray	(500 sq. ft. [46.5 sq.m])		(250 sq. ft. [23.23 sq.m])	

Note: Membrane rolls shipped horizontally on pallets, stacked pyramid-style and banded.

Storage Store rolls on their sides on pallets or shelving in a dry area.

Safety Warning Membrane rolls are heavy. Position and install by at least two people.

MONIER MALAYSIA SDN. BHD. (19163-M)
 Suite 12W, 12th Floor, Wisma FGV,
 Jalan Raja Laut, 50350 Kuala Lumpur
 T (+60) (3) 21760600 F (+60) (3) 26040335
 Toll Free: 1800 88 0865
 roofing-malaysia@bmgigroup.com
bmgigroup.com/my