

Environmentally-friendly boards made from natural wood fibres

Head of the second seco

AREAS OF USE

Multiple general usage in home or industrial applicactions

Also for industrial use.

- Standard quality with a smooth face
- Natural Fibre Board
- FSC certified material
- Multipurpose board for DIY, furniture, packaging and temporary structures
- Robust packing for protection and flatness

For more information please visit our website at www.steico.co.uk

Date 08/2016. Valid to subsequent revisions.

| PRODUCT RANGE AND PACKAGING

Туре	Thickness [mm]	Pieces/Pack	Standard sizes [mm×mm]	Coverage/Pallet [m²]	Weight/Palett [kg]
HB – genaral purpose	3.0	400	1220× 610	297	790
		150	1220 × 2440	446	1180
		150	1220×3050	558	1465
	6.0	200	1220× 610	148	840
		75	1220 × 2440	223	1235
		75	1220 × 3050	279	1555

| TECHNICAL SPECIFICATION

STEICO Hardboard HB – produced according to EN 622-2, Type HB

Proporty	Unit	Thickness [mm]		
Property		3.0	6.0	
Bending strength	N/mm²	30	25	
Internal bond	N/mm²	0.50	0.50	
Swelling in thickness	%	37	25	

| OTHER PROPERTIES

Thickness tolerances at the time of dispatch from factory - EN 622-1

Property	Unit	Thickness [mm]	
• •		3.0	6.0
Tolerance	mm	± 0.3	± 0.7

general properties at the time of dispatch from the factory - EN 622-1

Property	Limit		
Dimensional tolerances	± 2 mm/m; max ± 5 mm		
Squareness	2 mm/m		
Edge straightness	1.5 mm/m		
Moisture content	4 – 9 %		

- Fire class according to EN 13501-1: Class E
- The edges are butt jointed.
- FSC certified material









Operating site certified according to ISO 9001:2008



Your STEICO Distibutor