



MasterMatrix® VMA 362

Viscosity-Modifying Admixture

Description

MasterMatrix VMA 362 viscosity-modifying admixture (VMA) is a ready-to-use, liquid admixture that is specially developed for producing concrete with enhanced viscosity and controlled rheological properties. Concrete containing MasterMatrix VMA 362 admixture exhibits superior stability, thus increasing resistance to segregation and facilitating placement and consolidation. MasterMatrix VMA 362 admixture meets ASTM C 494/C 494M requirements for Type S. Specific Performance, admixtures.

Applications

Recommended for use in:

- Concrete containing "gapgraded" aggregates
- Lean concrete mixtures
- Concrete containing manufactured sand
- Concrete as a pumping aid
- Concrete as a finishing aid
- Concrete mixtures requiring "more body"
- Self-Consolidating Concrete (SCC)
- Liquid Sand program
- Pervious Concrete
- Self-Consolidating Grout
- Geotechnical grouting and ground improvement

Features

- Modifies viscosity of concrete
- Thixotropic properties

Benefits

- Controls bleeding
- Provides flexibility in mixture proportioning and batching
- Provides concrete stability during transport and placement
- Reduces segregation, even with highly fluid concrete mixtures
- Facilitates placement of pervious concrete mixtures
- Enhances pumping and finishing
- Enhances surface appearance
- Provides superior and predictable in-place concrete properties
- Facilitates production of highly fluid concrete mixtures such as self-consolidating concrete (SCC)

Performance Characteristics

Setting Time: Master Matrix VMA 362 admixture has little to no impact on concrete setting time within the recommended dosage range of 2 to 14 fl oz/cwt (130 to 910 mL/100 kg) of cementitious materials.

Compressive Strength: MasterMatrix VMA 362 admixture does not affect the compressive strength of concrete.

Viscosity: Concrete containing MasterMatrix VMA 362 admixture will exhibit an increase in viscosity with increasing dosage of the admixture. This desirable characteristic facilitates concrete placement, consolidation and finishing and provides stability to very fluid concrete mixtures.

Workability: Because of its thixotropic properties, concrete containing MasterMatrix VMA 362 admixture can increase in viscosity if left in a mixing vessel without agitation. Workability can be restored by simply remixing the concrete mixture.

Air Content: MasterMatrix VMA 362 admixture does not affect the air content in either air-entrained or non-air-entrained concrete. Typical dosages of air-entraining admixtures may be used to achieve the desired air content.

Guidelines for Use

Dosage: To provide stability in self-consolidating concrete (SCC) mixtures, the recommended dosage for MasterMatrix VMA 362 admixture is up to 14 fl oz/cwt (910 mL/100 kg) of cementitious materials. For other concrete mixtures that require "more body" to facilitate pumping and finishing, a dosage of up to 6 fl oz/cwt (390 mL/100 kg) is recommended. Because of variations in concrete materials, job site conditions and/or applications, dosages outside of the suggested range may be required. In such cases, contact your local sales representative.

Mixing: MasterMatrix VMA 362 admixture is typically added with the initial mix water. Alternately, MasterMatrix VMA 362 admixture may be added after all other concreting ingredients have been batched and thoroughly mixed, either at the batch plant or at the jobsite.

Product Notes

Corrosivity – Non-Chloride, Non-Corrosive: MasterMatrix VMA 362 admixture will neither initiate nor promote corrosion of reinforcing and prestressing steel embedded in concrete, or of galvanized steel floor and roof systems. Neither calcium chloride nor other chloride-based ingredients are used in the manufacture of this admixture.

Compatibility: MasterMatrix VMA 362 admixture is compatible with most admixtures used in the production of quality concrete including normal, mid-range and high-range water-reducing admixtures and air entrainers. MasterMatrix VMA 362 admixture is also compatible with typical accelerators, retarders, extended set-control admixtures, corrosion inhibitors, and shrinkage reducers. However, a field trial mixture is recommended to ensure appropriate performance.

Storage and Handling

Storage Temperature: MasterMatrix VMA 362 admixture must be stored at temperatures above 32 °F (0 °C) and below 130 °F (54 °C). Protect MasterMatrix VMA 362 admixture from freezing because it cannot be reconstituted after thawing.

Shelf Life: A product stability evaluation has shown that MasterMatrix VMA 362 admixture has a shelf life of 8 months. Please contact your local sales representative regarding suitability for use and dosage recommendations if the stated minimum shelf life of MasterMatrix VMA 362 admixture has been exceeded.

Dispensing: MasterMatrix VMA 362 admixture should be dispensed using direct-feed dispensing systems. It is recommended that fail-safe features must be included in this dispenser application for potential meter malfunctions. Consult your local sales representative for the proper dispensing equipment for MasterMatrix VMA 362 admixture.

Packaging

MasterMatrix VMA 362 admixture is supplied in 55 gal (208 L) drums, 275 gal (1040 L) totes, and by bulk delivery.

Related Documents

Safety Data Sheets: MasterMatrix VMA 362 admixture

Additional Information

For additional information on MasterMatrix VMA 362 admixture or its use in developing concrete mixtures with special performance characteristics, contact your local sales representative.

Master Builders Solutions creates technologies for the construction industry inspiring people to build better. We are active in \sim 40 countries and operate 35 production sites with over 1,600 employees. We develop, produce, and market high-quality chemical admixtures, as well as adjacent core technologies, to master the challenges of today and support a decarbonized future. Our people are pivotal and pair leading technologies and a strong brand heritage to surpass our customers' expectations and drive continuous value creation.

Limited Warranty Notice

Master Builders Solutions Admixtures US, LLC ("Master Builders Solutions") warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. MASTER BUILDERS SOLUTIONS MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders Solutions. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. MASTER BUILDERS SOLUTIONS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders Solutions' present knowledge and experience. However, Master Builders Solutions assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders Solutions reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

© Master Builders Solutions ■ 07/23 ■ DAT-0026
® registered trademark of Master Builders Solutions in many countries of the world

www.master-builders-solutions.com/en-us