

# MasterFlux 200

Post-tension cable grout

# **Material Description**

MasterFlux 200 is a high strength, pumpable grout specifically designed for civil engineering projects requiring durability and reliability. This advanced cementitious grout is formulated without aluminates, metallic expansion agents, or methocel-based additives, making it ideal for protection of high tensile steel elements.

Incorporating state-of-the-art superplasticisers and suspension agents, **MasterFlux 200** delivers exceptional fluidity and performance. Its innovative formulation ensures complete encapsulation of post-tension cables, preventing bleed, segregation, or voids, even in critical applications.

# **Areas of Application**

- Post-tension cable grouting ensures complete encapsulation and protection of steel cables.
- Rock bolting provides reliable anchorage in rock stabilization projects.
- General grouting suitable for filling voids and enhancing structural integrity.
- Soil and rock grouting improves ground stability and reduces permeability.
- Rock fissure grouting effectively seals fractures in rock formations.
- Precast grouting ensures strong, durable connections in precast concrete construction.
- Sand permeation used for consolidating loose sandy soils.

#### **Characteristics and Benefits**

- High compressive strength provides exceptional loadbearing capacity for demanding applications.
- Non-shrink properties ensures dimensional stability and eliminates voids for long-term durability.
- Excellent flowability easily placed in complex or congested areas
- High durability resistant to chlorides, sulphates, and freezethaw cycles, ensuring reliable performance in harsh environments.

- Pre-blended supplied as a single-component material, requiring only water for consistent mixing and application.
- Versatile applications suitable for structural grouting, void filling, anchoring, and critical repairs.
- Long-term performance minimizes maintenance costs with enhanced longevity and robust design.

### **Properties**

Tested Characteristic / Standard	Result		
Compressive strength AS 1478.2- Appendix A	Liter Water per 20 kg		
	<u>6.0 L</u>	<u>6.6 L</u>	<u>7.2 L</u>
24 hours: MPa	40	30	20
7 days: MPa	90	80	70
28 days: MPa	100	90	80
Bond Strength (by pull off)	0.5 - I.0MPa unprimed concrete 0.8 - I.5MPa primed concrete		
Chloride Content	<0.01%		
AS 1012.20			
Expansion	< 0.2% @ 30% water		
ASTM C940			
Change in Height	<0.18% @ 28 days		
ASTM C1090			
Bleeding	Zero @ 30% water		
ASTM C940			
Setting Time	Initial set – 240 minutes		
AS 1012.18	Final set – 300 minutes		
Fresh Wet Density	2100kg/m³ @ 30% water		
AS 1012.5	2000kg/m	3 @ 36% wate	er
Flow Characteristics	5-20 seconds (flow cone)		
AST478.2 Appendix C			
Change in Flow Characteristics	<3.0 seconds change in 45		
AS I 478.2 Appendix C	minutes		
Modulus of Elasticity	22.4 GPa		
AS1012.17			
Post Tensioning Requirements	Complies		
RMS R64	Complies		

Application Properties	Results	
Water addition	6.0 – 7.2 litres per 20kg	



# MasterFlux 200

Post-tension cable grout

Yield	12.2 litres per 20kg @ 30% water   12.8 litres per 20kg @ 33% water   13.4 litres per 20kg @ 36% water	
Pump Life	60-120 minutes	
Thickness range (mm)	Refer to Master Builders Solutions for	
	advice and approval on pour	
	thicknesses exceeding 100mm	
Maximum particle size	45 microns	

# **Application**

For information about application, please obtain a copy of the "Cementitious Grouts MasterFlux range" application guide from your local Master Builderes Solutions Technical Sales Representative or download a copy from the website. MasterFlux 200 may be poured or pumped into place. Check ducts and forms for leaks prior to mixing and application of grout. Mix at low speed during pumping and placement to maintain work life. High speed mixing should be avoided during placement to prevent temperature rise of the mixed grout.

#### **Mixing**

Measure and place approximately 90% of the desired water into the approved mixing vessel. Start mixer and slowly add MasterFlux 200.

Mix at high speed for a further 3 - 4 minutes to adequately dissolve the **MasterFlux 200** and achieve flowable consistency. Additional water can be added to a total volume not exceeding the total allowable limit.

#### **Pumping**

Once the grout has been mixed you need an effective pumping method to deliver it to the area of application. Various models of batch mixers and continuous mixers are available for use, all with varying specifications. It is important to match your application's specifics with the capabilities of the mixer and pump. Master Builders Solutions are able to recommend the right mixer for your project.

Once grout is mixed, it is important to keep it agitated continuously prior to pumping. Although, this product has a long pot life, if the grout is allowed to sit then it will 'gel' and may become more difficult to pump.

Once the site is ready for grout placement, commence pumping. It is important to pump continuously and avoid the formation of cold joints.

#### **Application Temperatures**

The mix water's temperature should be kept as low as possible to prevent the grout from hydrating too rapidly.

As with the water temperature, the higher the air temperature the more quickly the grout hydrates and sets. Master Builders Solutions specify mixing times and set times at an ambient temperature of 20°C. These times vary with temperature fluctuations, and adjustments will be required to compensate for this. Exposing the pumping hoses to the sun on a hot day accelerates the product's set time. In some cases it may be necessary to cool the material, the mix water, or even the hose itself during the process and pre-planning the storage of all materials to keep the temperature as low as possible.

High-shear mixing can add I to  $2^{\circ}$ C per minute of mixing. In order to minimise this effect, add all ingredients to the mixer as quickly as possible and minimise prolonged batch-mixing procedures.

### **Estimating Data**

One 20kg bag will yield approximately 12.2 - 13.4 litres :

MasterFlux 200					
20kg powder	Thickness in	m³	bags /m³		
Zokg powder	mm /m²				
30% water	12.2	0.0122	82		
33% water	12.8	0.0128	78		
36% water	13.4	0.0134	75		

### **Packaging**

**MasterFlux 200** is available in 20kg and bulk bags. Consult Master Builders Solutions for bulk supply or Ready mixed options.



# MasterFlux 200

Post-tension cable grout

# **Storage & Shelf Life**

Store in cool and dry warehouse conditions. Shelf life in these conditions is 12 months in unopened original bags.

#### **Precautions**

For the full health and safety hazard information and how to safely handle and use this product, make sure that you obtain a copy of the Safety Data Sheet (SDS) from our office or website.

# **Specification Clause**

PT CABLE GROUT - The ultra flow cementitious grout shall be a one component powder product which requires only the addition of water to form a durable ultra flow product. It shall be a pre-blended product that has independent testing to validate the performance

outlined in the technical data table on the following pages. The grout shall be free of aluminium and metallic expansion agents and methocel additives. MasterFlux 200 manufactured by Master Builders Solutions or equivalent shall be accepted.

#### **Disclaimer**

MasterFlux-200-ANZ-V2-1125

# STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this MB Solutions Australia Pty Ltd publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use and for ensuring that the application and use of the product is in accordance with the manufacturer's guidelines and recommendations.

#### NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by MB Solutions Australia Pty Ltd either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not MB Solutions Australia Pty Ltd, are responsible for carrying out procedures appropriate to a specific application.

MB Solutions Australia Pty Ltd ABN 69 634 934 419 Suite 102, 2 Burbank Place Norwest NSW 2153

Freecall: 1300 227 300

www.master-builders-solutions.com/en-au

MB Solutions New Zealand Ltd 45C William Pickering Drive Albany, Auckland New Zealand

Phone: +64 9 4l4 7233

Emergency Advice:

1300 954 583 within Australia (24hr) 0800 001 607 within New Zealand

