

# MasterRoc<sup>®</sup> MSL 345

## Waterproofing Membrane

### Description

MasterRoc MSL 345 is a sprayable membrane for waterproofing concrete structures. MasterRoc MSL 345 membrane is spray-applied between layers of sprayed or cast-in-place concrete. MasterRoc MSL 345 membrane exhibits high bond strength to the substrates on both sides of the membrane with good elasticity.

MasterRoc MSL 345 membrane can be directly applied to damp sections of substrate.

### Applications

Recommended for use in:

- Cast-in-place
- Composite-designed shotcrete sandwich structures (concrete or shotcrete/membrane/concrete or shotcrete)
- Underground structures with complex profiles and geometry
- Bonds to steel and most sheet membranes enabling interface solutions with other waterproofing methods

### Features

- Dry-process material, ready-for-use
- Elasticity 80-140% (depending on the temperature)
- Fast curing
- No toxic components
- Environmentally preferable

### Benefits

- Easily applied by spraying with standard dry-process shotcrete equipment
- Two-sided bond with sprayed-concrete allows for composite behavior
- Fast curing prevents disruption of construction operations
- The fully bonded system provides excellent watertightness, preventing development of water migration in both concrete membrane interfaces

### Compatibility

MasterRoc MSL 345 membrane can be applied onto all types of concrete, provided that the surface is clean and without loose particles. Sprayed concrete and cast-in-place concrete with or without steel fibers may be placed against the applied membrane surface, once it has cured.

MasterRoc MSL 345 membrane can also be applied in combination with traditional waterproofing sheet membrane system approaches.

## Performance Characteristics

### Technical Data

Form	Powder
Color	Light brown
Water pressure resistance	220 psi (15 bar)
Bulk density*	36.8 ± 6.2 lb/ft <sup>3</sup> (590 ± 100 g/L)
Consumption, per in. (mm) of thickness	5.2 lb/ft <sup>2</sup> (1.0 kg/m <sup>2</sup> )
Application thickness	0.12 - 0.40 in. (3 - 10 mm)
Application temperature	40 - 104 °F (5 - 40 °C)
Failure stress at 28 days*	220 - 500 psi (1.5 - 3.5 MPa)
Failure strain at 28 days*	> 100%
Bond strength at 28 days	175 ± 25 psi (1.2 ± 0.2 MPa)
Shore hardness	80 ± 5
Flammability	Non-flammable

\*at 68 °F (20 °C)

### Guidelines for Use

**Application:** If an external curing material has been applied to the shotcrete, it must be removed prior to applying MasterRoc MSL 345 membrane. Active water must be either presealed, collected through hoses in the membrane, or covered by drainage sheets fixed to the concrete surface, for diversion into a drainage system behind the membrane. For specific application information, please refer to the MasterRoc MSL 345 membrane Method Statement.

MasterRoc MSL 345 membrane should never be sprayed without the addition of water at the nozzle. Typical water content is between 60 and 70% by weight of product. The nozzle assembly must have a needle valve to allow for fine-tuning of the water and ball valve to stop and start the water flow.

**Spraying Technique:** Spraying distance of MasterRoc MSL 345 membrane should be between 5.0-6.5 ft (1.5-2.0 m) and spraying should be done in parallel strokes, followed by a second application layer at 90° to the first application.

**Note:** The nozzle should be manipulated in a way to assure full coverage of MasterRoc MSL 345 membrane into the surface texture of the substrate.

Depending on the roughness of the substrate, the consumption rate of MasterRoc MSL 345 membrane is approximately 5.2 lb/ft<sup>2</sup> per in. of thickness (1.0 kg/m<sup>2</sup> per mm of thickness). If the roughness of a shotcrete layer is too high, the placement of a smoothing or leveling layer of cementitious mortar [containing a maximum aggregate topsize of 0.16 in. (4 mm)] should be considered to provide a smooth

surface. This mortar layer will significantly reduce the consumption of MasterRoc MSL 345 membrane.

Shotcrete and cast-in-place concrete can be placed directly onto the MasterRoc MSL 345 membrane after sufficient curing has occurred.

**Cleaning:** Cleaning of the equipment can be accomplished by blowing compressed air through the system (aiming into the water). The nozzle and injector should be cleaned out with water.

### Equipment

It is recommended that MasterRoc MSL 345 membrane be applied by the dry spraying method using readily available dry spraying equipment like the Reed "Sove" pump.

Basic recommended equipment set-up:

- Rotor allowing low output (e.g., 18-pocket feedbowl)
- Rotor Dust collector
- Spraying nozzle diameter 1.25 in. (32 mm) (plastic tip with collar/conical) with minimum 16-hole water ring (18 holes recommended)
- Spraying hose diameter 1.25 in. (32 mm)

Suitable spraying equipment should be fitted with a dust collection filter. Care should be taken not to create excessive dust when filling the hopper of the machine. The floor areas near the machine should be soaked with water during the application process to bind dust.

### Storage and Handling

**Storage Temperature:** MasterRoc MSL 345 membrane should be stored in original, unopened bags at temperatures between 40 °F and 104 °F (5 °C and 40 °C). MasterRoc MSL 345 membrane should be kept out of direct sunlight and the storage area must be kept dry.

**Shelf Life:** MasterRoc MSL 345 membrane has a shelf life of 12 months if stored in original, unopened bags as recommended above. Depending on storage conditions, the shelf life may be greater than stated. Please contact your local sales representative regarding suitability for use if the shelf life of MasterRoc MSL 345 membrane has been exceeded.

**Safety:** It is recommended that gloves, eye protection and a dust mask be used when spraying MasterRoc MSL 345 membrane.

## Packaging

MasterRoc MSL 345 membrane is available in 44 lb (20 kg) and 33 lb (15 kg) bags.

## Related Documents

Safety Data Sheets: MasterRoc MSL 345 membrane

## Additional Information

For additional information on MasterRoc MSL 345 membrane, contact your local sales representative.

*Master Builders Solutions, a brand of MBCC Group, is a global leader of innovative chemistry systems and formulations for construction, maintenance, repair and restoration of structures. The Admixture Systems business provides advanced products, solutions and expertise that improve durability, water resistance, energy efficiency, safety, sustainability and aesthetics of concrete structures, above and below ground, helping customers to achieve reduced operating costs, improved efficiency and enhanced finished products.*

*Utilizing worldwide resources, the Master Builders Solutions community of experts are passionate about providing solutions to challenges within all stages of construction, as well as the life cycle of a structure. At Master Builders Solutions we create sustainable solutions for construction around the globe.*

## Limited Warranty Notice

Master Builders Solutions Admixtures US, LLC ("Master Builders Solutions") warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. MASTER BUILDERS SOLUTIONS MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders Solutions. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. MASTER BUILDERS SOLUTIONS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders Solutions' present knowledge and experience. However, Master Builders Solutions assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders Solutions reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.