

# MasterMatrix 360

High range water reducing admixture for concrete - EN 934-2: T3.1 & T3.2

## Material description

MasterMatrix 360 is an innovative superplasticiser featuring the latest generation range of polycarboxylic ether polymer. It contains a high-molecular weight synthetic copolymer particularly designed for the precast industry.

The particular molecular configuration of MasterMatrix 360 accelerates the cement hydration by allowing rapid adsorption of the molecule onto the cement particles, this, combined with an efficient dispersion effect, exposes increased surface of the cement grains to react with water exposing increased surface of the cement grains to react with water

The polymer structure of MasterMatrix 360 is specially designed to improve the rheology of precast concrete, making it very flowable and with low viscosity even at very low water/cement ratios, without increasing stickiness. Robustness is a distinctive feature of the precast concrete produced with MasterMatrix 360.

## Fields of application

MasterMatrix 360 is suitable for making precast concrete elements with highly-fluid concrete without segregation but low water/cement ratios and, consequently, high early and final strengths. Ecological and ergonomic precast production, MasterMatrix 360 is optimised for use with the Master X-Seed 100 Crystal Speed Hardening concept.

## Packaging

MasterMatrix 360 is supplied in Bulk, 1000-litre IBC's and 15-litre containers.

## Characteristics and benefits

MasterMatrix 360 offers the following benefits for the concrete industry:

- Production of highly flowable, robust self-compacting concrete having a low water cement ratio along with an optimal rheology.
- Enhanced robustness and consistency in concrete quality with low stickiness.
- Environmentally friendly, CO2 reduced mix-design optimization.
- Potential elimination or reduction of heat curing.
- Improved surface appearance.
- Durable precast concrete elements as per EN 206-1.
- Elimination or reduction of the energy required for placing, compaction and curing (ZERO ENERGY).
- Optimization of the curing cycles by reducing curing time or curing temperature. Increased productivity, particularly in combination with Master X-Seed 100 Crystal Speed Hardening.
- SCC (Self-compacting concrete) with a low Fines content (material passing the 0.125 mm sieve).

## Dosage

Field trials should be conducted to determine the optimum addition rates of MasterMatrix 360. As a starting point, the following dosage range is recommended.

- By Volume - 0.28 to 1.13 litres per 100 Kg of cement (binder)
- By Mass - 0.30 to 1.20 kg per 100 Kg of cement (binder)

# MasterMatrix 360

High range water reducing admixture for concrete - EN 934-2: T3.1 & T3.2

## Effects of Overdosing

The detrimental effects of an overdose of MasterMatrix 360 will depend upon the magnitude of the overdose in that an increase in initial setting time will occur. Provided the concrete is protected and cured, this will not necessarily result in any reduction in 28 day strength. The consistence (slump) of the concrete will be increased or the concrete will have a lower water content than the original mix design due to the additional plasticizing effects of the overdose. In addition to this there may be an increase in air entrainment. Depending on the level of the overdose it is possible that the concrete will have a higher tendency for segregation.

## Mixing

MasterMatrix 360 is a ready-to-use liquid admixture, which should be added to the concrete during the mixing process together with the water. This is particularly important in order to obtain maximum efficacy. For best performance it is advisable to dispense after 50 to 70% of the mixing water has been added & then continue mixing until the mix is completely homogeneous.

## Dispensing

MasterMatrix 360 should be dispensed through a proprietary dispenser. Details are available on request from our Technical Services Department.

## Compatibility

MasterMatrix 360 can be used with all types of EN 197 Cements. For use with other special cements, contact our Technical Services Department.

MasterMatrix 360 should not be pre-mixed with other admixtures. If other admixtures are to be used in concrete containing MasterMatrix 360 they must be dispensed separately. The rheological behaviour induced by MasterMatrix 360 may not require additional superplasticiser but should further workability be required it should be achieved with a MasterGlenium superplasticizer. It is incompatible for use with naphthalene sulphonate based superplasticizers.

# MasterMatrix 360

High range water reducing admixture for concrete - EN 934-2: T3.1 & T3.2

<b>Product Data</b>	
Appearance:	Cream / off white liquid
Specific gravity @ 20°C:	1.06 ± 0.02 g/cm <sup>3</sup>
pH-value:	6.5 ± 1
Alkali content (%):	≤ 1.00 by mass
Chloride content (%):	≤ 0.10 by mass
Corrosion behaviour:	Contains only components according to BS EN 934-1:2008, Annex A.1
Air Content:	Fulfilled
Water reduction:	≥ 112% of Reference mix
Increase in consistence:	Increase of ≥ 120mm from initial slump or ≥ 160mm from initial flow
Retention of consistence:	At 30 mins ≥ Reference mix at initial
Compressive strength:	Fulfilled
Durability:	NPD
Dangerous substances:	NPD
<b>Logistics</b>	
Shelf life:	12 months if stored according to manufacturer's instructions in unopened container.
Storage conditions:	Store in original sealed containers and at temperatures between 5°C and 30°C. Store under cover, out of direct sunlight and protect from extremes of temperature. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging.
Handling and transportation:	Refer to MasterMatrix 360 Safety Data Sheet
Disposal:	Refer to MasterMatrix 360 Safety Data Sheet

# MasterMatrix 360

High range water reducing admixture for concrete - EN 934-2: T3.1 & T3.2

## DISCLAIMER

MasterMatrix 360, Master Builders Solutions UK Ltd, Version 1

The following general comments apply to all products.

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs, (which may also be tainted with vapour until the product is fully cured and dried). Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Keep away from children and animals. Reseal containers after use.

**Health and Safety:** \*For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

**Spillage:** Chemical products can cause damage; clean spillage immediately.

## DISCLAIMER

"Master Builders Solutions UK Ltd" (the Company) endeavours to ensure that advice and information given in Product Data Sheets, Method Statements and Material Safety Data Sheets (all known as Product Literature) is accurate and correct. However, the Company has no control over the selection of its products for particular applications. It is important that any prospective customer, user or specifier, satisfies him/her-self that the product is suitable for the specific application. In this process, due regard should be taken of the nature and composition of the background/base and the ambient conditions both at the time of laying/applying/installing the material and when the completed work is to be brought into use. Accordingly, no liability will be accepted by the Company for the selection, by others, of a product, which is inappropriate to a particular application. Products are sold subject to the Company's standard conditions of sale and all customers, users and specifiers, should ensure that they examine the Company's latest Product Literature.

**UK  
CA**

0086-CPR-469071

**CE**

1073-CPR-7420

EN 934-2: T3.1 & T3.2

Declaration of Performance can be found at:  
[www.master-builders-solutions.com/en-gb](http://www.master-builders-solutions.com/en-gb)