

| | |
|----------|-------------------------------|
| 03 30 00 | Cast-in-Place Concrete |
| 03 40 00 | Precast Concrete |
| 03 70 00 | Mass Concrete |
| 31 00 00 | Earthwork |

MasterLife[®] ASR I 778

Water-Reducing and ASR Inhibiting Admixture

Description

MasterLife ASR I 778 admixture is formulated for use in concrete containing reactive aggregates to inhibit and control Alkali-Silica Reactivity (ASR). MasterLife ASR I 778 admixture is formulated to meet ASTM C 494/C 494M requirements for Type A Water-Reducing Admixtures.

Applications

Recommended for use in concrete mixtures containing reactive aggregates in the following applications:

- Large structures that are difficult to repair or replace
- Bridges, dams, stadiums, buildings
- Concrete pavements
- Structures with long design service lives

Features

- Ready-to-use liquid admixture
- Capable of mitigating ASR (Alkali-Silica Reaction) in concrete containing highly reactive aggregates
- Effective with cements of varying alkali content


Benefits

- Improves durability of concrete
- Allows the use of locally available aggregates
- Extended service life of concrete structures

Performance Characteristics

Mitigation of Alkali-Silica Reactivity (ASR): MasterLife ASR I 778 admixture has shown to be effective in mitigating ASR in concrete using a modified ASTM C 1567 Accelerated Mortar-Bar Method.

The example data shown in the graphic indicates an expansion of less than 0.10% in mortar treated with MasterLife ASR I 778 admixture that contains highly reactive aggregates.



Guidelines for Use

Dosage

The dosage of MasterLife ASR 1778 admixture is based on the reactivity level of the aggregates and is determined by evaluating the aggregates using a modified ASTM C 1567 test method. MasterLife ASR 1778 admixture is recommended for use within a dosage range of 1 – 6 gal/yd³ [5 – 30 L/m³] of concrete.

Note 1: Some supplementary cementitious materials (SCMs) such as silica fume, slag cement, and some types of fly ash do provide a benefit in mitigating ASR in concrete. Therefore, the dosage of MasterLife ASR 1778 admixture in a SCM-treated concrete mixture may be reduced if testing is performed (a) to establish the beneficial effect of the SCM and (b) to determine the optimum dosage of MasterLife ASR 1778 admixture required for the concrete mixture. Testing is required if a significant amount of alkalis can be contributed by sodium-bearing admixtures or Class C fly ash that are a part of the concrete mixture. For additional information on testing and dosages of MasterLife ASR 1778 admixture in SCM-treated or other concrete mixtures, please contact your local sales representative.

Water Content

For every gallon of MasterLife ASR 1778 admixture, the mix water content should be reduced by 0.55 gal (1.9 L) to maintain the designed water-cementitious materials ratio.

Dispensing and Mixing

MasterLife ASR 1778 admixture may be added to the concrete mixture during the initial batch sequence at the production plant. Mixing at high speed for 3–5 minutes after the addition of MasterLife ASR 1778 admixture will result in mixture uniformity.

Product Notes

Corrosivity - Non-Chloride, Non-Corrosive: MasterLife ASR 1778 admixture will neither initiate nor promote corrosion of reinforcing steel, prestressing steel or of galvanized steel floor and roof systems. Neither calcium chloride nor other chloride-based ingredients are used in the manufacture of MasterLife ASR 1778 admixture.

Compatibility - Admixtures: MasterLife ASR 1778 admixture is compatible with most admixtures used in the production of quality concrete, including normal, mid-range and high-range water-reducers, retarders, accelerators and corrosion inhibitors. For air-entrained concrete applications, MasterLife ASR 1778 admixture is recommended for use with high-range water-reducing admixtures, such as the MasterGlenium® series, for maximum workability while maintaining a low water-cementitious materials ratio. MasterLife ASR 1778 admixture can also be used with MasterAir® series of air-entraining admixtures. The dosage of air-entraining admixture shall be established through truck trial.

Compatibility - Cementitious Materials: MasterLife ASR 1778 admixture can be used with portland cements approved under ASTM, AASHTO or CRD specifications and supplementary cementitious materials used in concretes. Trial mixes with MasterLife ASR 1778 admixture is required before project start to ensure compatibility and desired results, especially due to potential variations in material response. Different sources of cementitious materials and variations between material batches may affect setting time, slump, or other performance attributes including compressive strength. Consult your local sales representative for recommended concrete mixture adjustments if necessary.

Storage and Handling

Storage Temperature: MasterLife ASR 1778 admixture should be stored at ambient temperatures above 40 °F (5 °C), and precautions should be taken to protect the admixture from freezing. If MasterLife ASR 1778 admixture freezes, thaw and reconstitute by mild mechanical agitation. Do not use pressurized air for agitation.

Packaging

MasterLife ASR 1778 admixture is available in 275 gal (1041 L) totes and by bulk delivery.

Shelf Life

MasterLife ASR 1778 admixture has a minimum shelf life of 12 months when stored under recommended conditions. Depending on storage conditions, the shelf life may be greater than stated. Please contact your local sales representative regarding suitability for use if the shelf life of MasterLife ASR 1778 admixture has been exceeded.

Related Documents

Safety Data Sheet: MasterLife ASR 1778 admixture

Additional Information

For additional information on MasterLife 300L admixture, or its use in developing a concrete mixture with special performance characteristics, contact your local sales representative.

Master Builders Solutions creates technologies for the construction industry inspiring people to build better. We are active in ~40 countries and operate 35 production sites with over 1,600 employees. We develop, produce, and market high-quality chemical admixtures, as well as adjacent core technologies, to master the challenges of today and support a decarbonized future. Our people are pivotal and pair leading technologies and a strong brand heritage to surpass our customers' expectations and drive continuous value creation.

Limited Warranty Notice

Master Builders Solutions warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. MASTER BUILDERS SOLUTIONS MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders Solutions. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. MASTER BUILDERS SOLUTIONS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders Solutions' present knowledge and experience. However, Master Builders Solutions assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders Solutions reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.