

MasterFiber 143

Structural synthetic fibre for reinforcement in cast and sprayed concrete applications as an alternative and/or supplement to existing concrete reinforcement products

Material Description

MasterFiber 143 is engineered for use as secondary reinforcement to control hardened shrinkage, temperature, and settlement cracking.

MasterFiber 143 is an option for the replacement or supplementation of steel mesh reinforcement and is an easy-to-use secondary reinforcement system that is rust proof and alkali resistant.

MasterFiber 143 conforms to the requirements of EN 14889.2 Class II.

Areas of Application

MasterFiber 143 applications include, but are not limited to:

- Slabs on ground: footpaths, shared user paths, industrial floors, and hardstands
- Precast: Pits, troughs, tanks, and panels
- Shotcrete: Civil slope stabilization

Characteristics & Benefits

- Allows for full or partial substitution of steel mesh reinforcement
- Reduces labour, construction, transport, and storage costs compared to a solution with conventional reinforcement
- Improves concrete ductility and energy absorption
- Provides increased flexural toughness to the concrete and decreases crack occurrence due to constrained deformation and impact
- Enables carbon reduction within the concrete element
- Provides a rust-free reinforcing solution
- Excellent resistance in alkaline and acidic environments
- Easy to dose either at the batch plant or on-site concrete mixer truck prior to application
- Safe to handle and no negative impacts on machinery wear

Properties

Polymer type	Virgin polypropylene
Sectional shape	Rectangular
Longitudinal shape	Embossed
Length	47 mm
Equivalent diameter	0.95 mm
Aspect ratio	49
Ultimate tensile strength	550 MPa
Young's modulus	10 GPa
Density	910 kg/m ³
Melting point	Approx. 170°C
Acid/alkali resistance	High

Dosing & Batching

The typical dose rate of **MasterFiber 143** is 4.0 – 6.0 kg/m³.

MasterFiber 143 is packed in mulchable boxes that can be added directly to the concrete mixer. It is recommended to add fibre into a zone of sufficient shear to aid in fast fibre distribution through the mix.

After the addition of **MasterFiber 143** to the mix, it is recommended to mix for a minimum of 120 – 180 seconds. High fibre dosages may require a longer mixing time in order to achieve sufficient dispersion.

The mechanical performance of **MasterFiber 143** is influenced by the mix design and cementitious materials used. Preliminary tests under practical conditions with regards to mixing and casting are advised for a proper assessment.

Packaging

MasterFiber 143 comes in 2.5 kg and 5.0 kg mulchable boxes.

MasterFiber 143 is wrapped in water-soluble PVA to form bundles to aid in concrete mix dispersion.

MasterFiber 143

Structural synthetic fibre for reinforcement in cast and sprayed concrete applications as an alternative and/or supplement to existing concrete reinforcement products

Storage & Shelf Life

MasterFiber 143 should be stored undercover in a clean, dry area, protected from the weather. Use caution when stacking to avoid unstable conditions.

Note

Field service support, where provided in no way constitutes supervisory responsibility. For additional information please contact your local Master Builders Solutions representative. MB Solutions reserves the right to have the true cause of any technical challenge determined by accepted test method.

Disclaimer

MasterFiber_143-ANZ-V7-0226

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this MB Solutions Australia Pty Ltd publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use and for ensuring that the application and use of the product is in accordance with the manufacturer's guidelines and recommendations.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by MB Solutions Australia Pty Ltd either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not MB Solutions Australia Pty Ltd, are responsible for carrying out procedures appropriate to a specific application.

MB Solutions Australia Pty Ltd

ABN 69 634 934 419
Suite 102, 2 Burbank Place
Norwest NSW 2153

Freecall: 1300 227 300

www.master-builders-solutions.com/en-au

MB Solutions New Zealand Ltd

45C William Pickering Drive
Albany, Auckland
New Zealand

Phone: +64 9 414 7233

Emergency Advice:

1300 954 583 within Australia (24hr)
0800 001 607 within New Zealand

