

# MasterCO<sub>2</sub>re 5700

Superplasticizer based on the Intelligent Cluster System (ICS) Technology for low clinker concrete production – BS EN / EN 934-2: T3.1 & T3.2

## Material description

MasterCO<sub>2</sub>re 5700 is an innovative superplasticizer, based on the Intelligent Cluster System (ICS) Technology, developed in the R&D Laboratories of Master Builders Solutions. Ideal for making precast elements with highly-fluid concrete without segregation. This technology allows low water/cement ratios and consequently, high early and final strengths. MasterCO<sub>2</sub>re 5700 combines the performances of fluidification, extended workability retention with superior rheology, in one single solution.

MasterCO<sub>2</sub>re 5700 provides the perfect choice for stable and robust concrete performance in challenging low-clinker applications, paving the way for a more responsible future in the construction industry.

## Fields of application

MasterCO<sub>2</sub>re 5700 is especially engineered for precast concrete applications providing fluid consistency and for self-compacting concrete, to impart exceptional rheological properties and ensure exceptional workability retention, in all curing conditions.

## Packaging

MasterCO<sub>2</sub>re 5700 is supplied in Bulk, 1000-litre IBC's and 15-litre containers.

## Characteristics and Benefits

MasterCO<sub>2</sub>re 5700 offers the following main benefits:

**Unmatched robustness:** With rapidly changing cement types and binder compositions, the stability and quality consistency of concrete is a challenge in the daily operations of concrete plants. MasterCO<sub>2</sub>re 5700 successfully counteracts the potential of high-water absorption and other undesirable effects caused by the variation in chemical and mineralogical composition of the binders.

**Advanced rheology:** concrete with MasterCO<sub>2</sub>re 5700 has lower viscosity allowing easier placement, passing ability and resistance to segregation. Thanks to this superior rheology, the content of water can be further reduced without compromising the stability even in concrete mixes with reduced clinker amount.

**Extended workability retention:** thanks to the Intelligent Cluster System technology, MasterCO<sub>2</sub>re 5700 releases the polymer over time, ensuring consistent flowability and workability during the transportation and placing of concrete. MasterCO<sub>2</sub>re 5700 offers the solution 365 days a year; as the workability retention is achieved without retardation in setting and hardening.

**Excellent strength properties:** MasterCO<sub>2</sub>re 5700 promotes the formation of a denser and more homogeneous structure of cement hydrates, which is reflected into optimal strengths development.

# MasterCO<sub>2</sub>re 5700

Superplasticizer based on the Intelligent Cluster System (ICS) Technology for low clinker concrete production – BS EN / EN 934-2: T3.1 & T3.2

## The Intelligent Cluster System (ICS) Technology

MasterCO<sub>2</sub>re 5700, thanks to its Intelligent Cluster System (ICS), can immediately release a portion of its available engineered polymers for initial water reduction. The finely tuned chemical structures of the diverse clusters adapt the release mechanism of the polymers to the characteristics of the cement matrix, thereby optimizing both workability retention and cement hydration. In this way, MasterCO<sub>2</sub>re 5700 successfully controls the absorption rate and ensures consistently high performance of the concrete.




Fig. 2 Overall performance of MasterCO<sub>2</sub>re 5700

## Simplifying the production of low-clinker concrete

Reducing the clinker content in concrete is a necessary measure, to achieve the current challenges of CO<sub>2</sub> reduction. Low-clinker concrete can be produced through three main routes:

- Switching to a cement with reduced CO<sub>2</sub> emissions; keeping the cement dosage at the lowest possible value, while ensuring the achievement of the desired strengths; including high amounts of supplementary cementitious materials (SCM) in the concrete mix.
- Providing improved workability retention, advanced rheology, and excellent strength properties,

MasterCO<sub>2</sub>re 5700 mitigates the well-known challenges associated with the production of low-clinker concrete, thereby supporting the Concrete Industry to achieve the Sustainability targets, without compromising on quality.

- As compared to the state-of-the-art admixture technology, MasterCO<sub>2</sub>re 5700 allows for further water reduction, without negative impact on rheology. The effect of reduced cement paste is offset by the rheological improvement of MasterCO<sub>2</sub>re 5700.

## Dosage

The recommended dosage rate for MasterCO<sub>2</sub>re 5700 range is 0.5 to 2.0 litres per 100 kg of binder and depends on the desired water reduction and workability retention. Other dosages may be recommended in special cases, according to specific job site conditions. In such cases, please consult our Technical Service Department for advice.

## Storage

MasterCO<sub>2</sub>re 5700 must be stored in a place where the temperature does not drop below 5 °C.

## Directions for use

MasterCO<sub>2</sub>re 5700 is a liquid admixture to be added to the concrete during the mixing process:

- Mix cement and secondary binders, sand, coarse aggregates and the mix water until a stiff, yet homogeneous, mixture is obtained.
- Optimal mixing water reduction is obtained if MasterCO<sub>2</sub>re 5700 is mixed into the concrete right after the addition of the initial 80-90% of the total water.

# MasterCO<sub>2</sub>re 5700

Superplasticizer based on the Intelligent Cluster System (ICS) Technology for low clinker concrete production – BS EN / EN 934-2: T3.1 & T3.2

<b>Technical Information</b>	
Form	Yellow liquid
Relative density (g/cc at 20°C)	1.04 – 1.08
pH	10 – 12
<b>Essential characteristic in accordance to EN 934-2 Performance</b>	
Chloride ion content	≤ 0.1% by mass
Alkali content (Na <sub>2</sub> O equivalent)	≤ 1.0%
Corrosion behaviour	Contains only components from EN 934-1 2008 Annex I
Compressive strength	Equal consistence: 1 day ≥ 140%; 28 days ≥ 115% Equal w/c ratio: 28 days ≥ 90%
Air content	Equal consistence: ≤ 2.0 % above control Equal w/c ratio: ≤ 2.0 % above control
Water reduction	≥ 12%

# MasterCO<sub>2</sub>re 5700

Superplasticizer based on the Intelligent Cluster System (ICS) Technology for low clinker concrete production – BS EN / EN 934-2: T3.1 & T3.2

## DISCLAIMER

MasterCO<sub>2</sub>re 5700, Master Builders Solutions UK Ltd, Version 3

The following general comments apply to all products.

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs, (which may also be tainted with vapour until the product is fully cured and dried). Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Keep away from children and animals. Reseal containers after use.

**Health and Safety:** \*For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted. **Spillage:** Chemical products can cause damage; clean spillage immediately.

**DISCLAIMER:** "Master Builders Solutions UK Ltd" (the Company) endeavours to ensure that advice and information given in Product Data Sheets, Method Statements and Material Safety Data Sheets (all known as Product Literature) is accurate and correct. However, the Company has no control over the selection of its products for particular applications. It is important that any prospective customer, user or specifier, satisfies him/her-self that the product is suitable for the specific application. In this process, due regard should be taken of the nature and composition of the background/base and the ambient conditions both at the time of laying/applying/installing the material and when the completed work is to be brought into use. Accordingly, no liability will be accepted by the Company for the selection, by others, of a product, which is inappropriate to a particular application. Products are sold subject to the Company's standard conditions of sale and all customers, users and specifiers, should ensure that they examine the Company's latest Product Literature.



24

EN 934-2: T3.1 & T3.2

Declaration of Performance can be found at:  
[www.master-builders-solutions.com/en-gb](http://www.master-builders-solutions.com/en-gb)

### Master Builders Solutions UK Ltd

Swinton Hall Road, Swinton, Manchester, M27 4EU  
Tel: +44 (0) 161 727 6300  
[www.master-builders-solutions.com/en-gb](http://www.master-builders-solutions.com/en-gb)

Master Builders Solutions UK Ltd  
Swinton Hall Road, Swinton, Manchester, M27 4EU  
Tel: +44 (0) 161 727 6300  
[www.master-builders-solutions.com/en-gb](http://www.master-builders-solutions.com/en-gb)

