

# MasterCrete CI 5300

Cementitious Lightweight, mid strength, polymer modified, fibre reinforced, structural repair mortar with active corrosion inhibition

## Material Description

**MasterCrete CI 5300** is a single component, lightweight, polymer modified, high build structural repair mortar with active corrosion inhibition. **MasterCrete CI 5300** has been specifically formulated to produce a mortar with the compressive strength and modulus characteristics defined in class R3 and R4 of EN 1504 part 3.

## Areas of Application

**MasterCrete CI 5300** is used for the structural repair of lower strength concrete elements such as balcony edges, soffits and decks, window ledges, lintels and beams or anywhere where concrete structures need to be repaired or re-profiled by hand.

## Characteristics and Benefits

- Shrinkage compensation and fibre reinforcement - minimise crack tendency creating a longer lasting repair
- Medium strengths - allows the repair of medium strength concrete without problems of differential movement
- Highly thixotropic and lightweight - allows single high build layers
- High build - applied up to 75 mm in vertical applications and 50 mm overhead
- Outstanding workability - easy to create profiles and corners without formwork
- Very low shrinkage - excellent crack resistance
- Durable and weather resistant - good water and chloride impermeability
- Low chromate ( $\text{Cr[VI]} < 2 \text{ ppm}$ ) - low risk of skin irritation
- Chloride-free - does not add to chloride load of contaminated structures
- Active corrosion inhibition – suitable for extreme environments.
- Carbonation resistant- 1 mm of MasterCrete CI 5300 provides carbonation resistance equivalent to approximately 6mm of standard 40 MPa concrete.
- Approved to AS/NZS 4020:2018 (tested to the maximum exposure level) - suitable for contact with potable water.

## Properties

### Technical Properties

Technical Characteristics	Test Method	Test results
Bond Strength-MPa	AS 1012.24	> 1.5
Compressive Strength-MPa	AS 1478.2 App. A	1 day: 19 7days: 40 28days:48
Modulus of Elasticity-GPa	AS1012.17	28days: 24.7
Carbonation Resistant	EN 13295	2.8 mm
Capillary absorption $\text{kg/m}^2\text{h}^{0.5}$	EN 13057	$\leq 0.5$
Chloride Content	AS1012.20	0.012%
Fresh Wet Density - $\text{kg/m}^3$	AS1012.5	1783
Indirect Tensile Strength -MPa	AS1012.18	28days: 4.3
Flexural Strength -MPa	ASTM C348	28days: 6
Setting time-min	AS1012.18	Initial: 210 Final:329
Drying Shrinkage- $\mu$ strain	AS1012.13	7d: 130 21d: 270 56d: 210
Sulphate content	AS1012.20.1	0.71%
Chloride Diffusion- $\text{m}^2/\text{sec}$	Nordtest NT Build 443	5.29E-12
Electrical Resistivity - $\text{K}\Omega\cdot\text{cm}$	AASHTO T358	28days:49.9

All data provided in technical characteristics table verified through testing conducted by NATA-accredited independent laboratories, in full accordance with the specified test methods.

### General Properties

Appearance	Grey powder
Water added per bag	3.8 to 4.2 litres per 20kg
Colour	Grey
Storage temperature	5-35°C
Temperature for application (substrate and material)	+5°C to +35°C

# MasterCrete CI 5300

Cementitious Lightweight, mid strength, polymer modified, fibre reinforced, structural repair mortar with active corrosion inhibition

## Application

For detailed application methodology, please refer to "Cementitious Concrete Repair MasterCrete Repair Mortars" Application Guide.

### Surface Preparation

Concrete must be fully cured with a minimum direct tensile strength of 1.0 MPa. All loose concrete or mortar, dust, grease, oil and curing compounds must be mechanically removed. Aggregate should be clearly visible on the surface of the concrete structure after preparation.

Non-impact/vibrating cleaning methods, e.g. grit or high water pressure blasting are recommended to obtain a CSP 5 or greater profile. Cut the edges of the repair vertically to a minimum depth of 5 mm. Clean all exposed reinforcement to a minimum grade of Sa 2 according to ISO 8501-1 / ISO 12944-4. In case of chloride contamination of the concrete, when depth of cover is less than 5 mm or when the steel is left exposed before the repair work is completed, the reinforcement should be protected by using MasterCrete PRI 5000.

### Mixing

Only full bags are mixed. Damaged or opened bags should not be used. Mix MasterCrete CI 5300 with clean water only, in a forced action pan mixer, or with a helical paddle attached to a slow speed (300-600 rpm) mixer for 3 minutes until the required lump-free, plastic consistency is achieved. Mixing water needed: 3.8 to 4.2 litres per 20kg bag depending upon consistency required. Allow the mortar to rest for 2 - 3 minutes and then remix briefly, adjusting the consistency as required, without exceeding the maximum water demand.

### Priming Concrete

The prepared substrate should be pre-soaked, preferably for 24 hours, but at least 2 hours before applying MasterCrete CI 5300. The surface must be saturated surface dry, but without standing water. To obtain extra strong bonding, the damp substrate can be primed with a slurry brush coat of MasterCrete CI 5300 (2 parts powder to 1 part water) or

MasterCrete PRI 157. Alternatively, MasterCrete PRI 5000 can also be applied as the bonding slurry.

### Mortar Application

The minimum temperatures must be maintained during application and for at least 24 hours thereafter for optimum curing of the product. MasterCrete CI 5300 can be hand, trowel or spray applied. Apply mixed product directly to the prepared damp substrate, or wet in wet onto the primed surface.

A thin scrape coat or contact layer before building up to the required thickness, wet on wet, will improve the wet adhesion and cohesion of the mortar, especially in case of hand application. Apply to the desired layer thickness of 5 to max 75 mm and level using a screeding beam, trowel or wooden board. Can be applied in thicker layers in smaller patches or where additional reinforcement is present. Smoothing with a trowel or finishing by float or sponge can be done as soon as the mortar has begun to stiffen.

### Curing

The following curing methods are advised - polyethylene film, damp cloths, MasterKure curing agent.

### Estimating Data

One 20kg bag will yield approximately 12.4 litres of mortar. Approx. 2.0 kg of mixed product per m<sup>2</sup> and mm layer thickness (approx. 1.8 kg of dry powder per m<sup>2</sup> and mm layer thickness).

MasterCrete CI 5300				
L	Thickness in mm /m <sup>2</sup>	m <sup>3</sup>	bags /m <sup>3</sup>	m <sup>2</sup> /mm thickness
12.4	12.4mm	(0.0124)	81	12.4 m <sup>2</sup>

### Packaging

MasterCrete CI 5300 is available in 20kg bags.

# MasterCrete CI 5300

Cementitious Lightweight, mid strength, polymer modified, fibre reinforced, structural repair mortar with active corrosion inhibition

## Storage & Shelf Life

Store in cool and dry warehouse conditions. Shelf life in these conditions is 12 months in unopened original bags.

## Precautions

For the full health and safety hazard information and how to safely handle and use this product, make sure that you obtain a copy of the Safety Data Sheet (SDS) from our office or website.

## Disclaimer

MasterCrete-CI 5300-ANZ-V3-I 125

### STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this MB Solutions Australia Pty Ltd publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use and for ensuring that the application and use of the product is in accordance with the manufacturer's guidelines and recommendations.

### NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by MB Solutions Australia Pty Ltd either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not MB Solutions Australia Pty Ltd, are responsible for carrying out procedures appropriate to a specific application.

#### MB Solutions Australia Pty Ltd

ABN 69 634 934 419  
Suite 102, 2 Burbank Place  
Norwest NSW 2153

Freecall: 1300 227 300

[www.master-builders-solutions.com/en-au](http://www.master-builders-solutions.com/en-au)

#### MB Solutions New Zealand Ltd

45C William Pickering Drive  
Albany, Auckland  
New Zealand

Phone: +64 9 414 7233

#### Emergency Advice:

1300 954 583 within Australia (24hr)  
0800 001 607 within New Zealand