

Seryap[®] 132 (MasterFlux[™] TIL 132)

Cement Based Ceramic and Marble Adhesive (Coarse Gradation)

Material Description

Seryap[®] 132 is a cement based highly stable adhesive used in adhesion of ceramics, and marbles.

Complies with the EN 12004 - C1T class.

C1= Normally hardening cement based adhesive
T= With reduced sliding

Areas of Application

- Indoor and outdoor areas for vertical and horizontal applications
- In the adhesion of tiles, ceramics, marbles, decorative tiles or press bricks, and cottos to cement based surfaces.

Characteristics and Benefits

- Easy to prepare and apply.
- Long process time.

- No sliding in vertical applications.
- No slump
- High adhesion property

Processing Method


(A) Preparation of Substrate

Application surface has to be strong, dry, bearing, dustless, clean, and also in balance. Surface must be cleaned off all kinds of oil, grease, rust, and paraffin traces that can weaken adherence and no loose particles must be present. Disordered surface with 5 to 20 mm depth must be repaired with **MasterCrete[™] S88 C** repair mortars two days before the application. If the application surface is over +25°C, then it must be moisturized.

(B) Mixing

Necessary amount of water is poured into a clean mixing container with the help of a scale. **Seryap[®] 132**

Technical Properties

Structure of the Material	Mineral Sealants, Synthetic Additives and Special Cement	
Color	Gray, White	
Tensile Adhesion Strength	≥0,50 N/mm ² (28 days)	
Application Thickness	Min. 4 mm Max. 15 mm	
Joint Sealant Period	24 hours	
Application Ground Temperature	+5°C +25°C	<div>WK</div> 
Service Temperature	-20°C +80°C	
Maturity Period	3-5 minutes	
Usage Period	2 hours	
Period of Open Waiting	20 minutes	
Slide (mm)	≤ 0,5 mm	
Wetting Ability	Min. 90 %	
Walkable After	24 hours	

The above values are given for +23°C and 50% relative humidity. High temperatures shorten the time, low temperatures lengthen the time.

Seryap® 132 (MasterFlux™ TIL 132)

Cement Based Ceramic and Marble Adhesive (Coarse Gradation)

is slowly added to the water and mixed with a 400-600 RPM mixer for 3-5 minutes until a homogenous and unumpy mixture is obtained. After resting it for approximately 3-5 minutes and mixing again for 30 seconds, the material is ready to use.

Mixing Ratio

Seryap® 132	Amount of Mixture Water
For 1 kg powder	~0,22 liter
For 25 kg bag	~5,50 liter

(C) Processing

1 mm **Seryap® 132** is applied on application surface with the flat side of trowel. In an area that can be covered in 20 minutes, period of open waiting, **Seryap® 132** is applied by serrated side of trowel in single direction in uniform thickness. In the adhesion of ceramics or granites with different thicknesses, to repair the disorder on application surface, it is suggested to apply 1 mm mortar under each ceramic or granite. When applying ceramics or granites to the place of application, ceramics or granites are floated on mortar to enable full contact of adhesion mortar. Suggested joint gap according to applied ceramic or tile dimension is left and the application is finished. To fill the left joint gaps, **MBT Tech** joint grouts must be used. Grouting of joints can be realized after approximately 24 hours.

Suggested Reed Dent Dimensions

Ceramic Dimensions	Ceramic Notched Trowel Dimensions	Mortar Bedding Thicjness
Up to 30 cm x 30 cm	8 mm	~ 3 mm
Over 30 cm x 30 cm	10 mm	~ 4 mm

Suggested Joint Width

Up to 5 cm x 5 cm	3 mm
Up to 15 cm x 15 cm	4 mm
Over 15 cm x 15 cm	6-8 mm

Consumption

1.33 kg/m² for a thickness of 1 mm adhesive

Seryap® 132	Ceramic Notched Trowel Dimensions and Coverage (kg/m ²)	
	8 mm	10 mm
25 kg	5,31	6,64

Applicability Test of Adhesive (Period of Open Waiting)

Fingers are pressed on the adhesive applied surface. If the adhesive smeared on the fingers, application of ceramics or granites is continued. If the fingers are clean, it means the application time of adhesive has passed. In this case, the adhesive is scraped off the surface and new adhesive is applied.

Point to Consider

- If environmental temperature is below +5°C or over +25°C in **Seryap® 132** application, then suitable temperatures must be waited for. Also **Seryap® 132** application should not be made in very hot, rainy or windy weathers.
- Seryap® 132's** spread thickness must not exceed 15 mm (min. 4 mm). Ceramics with high water absorption have to be watered well before application.
- Under no circumstances, water and new material must be added to drying **Seryap® 132** mixture.

Seryap® 132 (MasterFlux™ TIL 132)

Cement Based Ceramic and Marble Adhesive (Coarse Gradiation)

Cleaning of Tools

All the tools and equipments must be cleaned by water after the application. After **Seryap® 132** is hardened, it can only be removed from the surface mechanically.

Packaging

Seryap® 132 is available in 25 kg polyethylene reinforced kraft bag.

Shelf Life

12 months if stored according to manufacturer's instructions in unopened container. Opened packages have to be stored by tightly sealing the bag, and must be used in one week.

Storage

Must be stored in unopened original packing, and in cool and dry environment protected from freezing. In short-term storing, maximum 3 palettes can be stowed on top of each other and delivery has to be according to first in first out system. In long-term storing, the palettes must not be stowed on top of each other.

Health and Safety

It is dangerous to approach the application sites. During the application, a protective apparel, protective gloves, goggles and masks which comply with the Occupational Health and Safety Rules should be used. Due to the irritation effect of the uncured materials, the mixture should not come into contact with skin and eyes; in case of a contact, the affected area should be washed with plenty of water and soap; in case of swallowing, a physician should be consulted immediately. No food or beverages should be brought to the application area. The product should be stored and kept out of reach of children. For detailed information please consult the Material Safety Data Sheet.

Disclaimer

The technical information given in this publication is based on the present state of our best scientific and practical knowledge. **MBT Teknik Yapı Kimyasalları Sanayi ve Ticaret A.Ş.** is only responsible for the quality of the product **MBT Teknik Yapı Kimyasalları Sanayi ve Ticaret A.Ş.** is not responsible for results that may occur because the product is used other than advised and/or out of instructions regarding the place and the method of use. This technical form is valid only till a new version is implemented and nullifies the old ones.

Contact

MBT Teknik Yapı Kimyasalları San. ve Tic. A.Ş.
Eyüp Sultan Mah. Sekmen Cad. Hayy 1000A
No:26/8 Sancaktepe, İstanbul
Tel: 0216 561 35 45 www.mbt-tech.tr

Seryap® 132 (MasterFlux™ TIL 132)

Cement Based Ceramic and Marble Adhesive (Coarse Gradation)

CE	
MBT TEKNİK YAPI KİMYASALLARI SAN. VE TİC. A.Ş.	
Eyüp Sultan Mah. Sekmen Cad. HAYY 1000A No:26 K:5 D:8, 34885 Sancaktepe, İstanbul, Türkiye	
25	
DOP NO 2201003	
TS EN 12004 - C1T	
Seryap® 132 (MasterFlux™ TIL 132)	
Kayma Özelliği Azaltılmış Normal Sertleşen İç ve Dış Kullanım İçin Uygun Çimentolu Yapıştırıcı (Normal hardening cement adhesive for Internal and External use with reduced slip feature)	
Yangına Karşı Tepki (Reaction To Fire)	A1
Başlangıç Çekme Yapışma Kuvveti (Initial tensile adhesion strength)	≥ 0,5 N /mm²
Isı ile yaşlandırıldıktan sonra çekme yapışma kuvveti (Tensile adhesion strength after heat ageing)	≥ 0,5 N /mm²
Suya daldırıldıktan sonra çekme yapışma kuvveti (Tensile adhesion strength after water contact)	≥ 0,5 N /mm²
Donma-çözünme çevriminden sonra çekme yapışma kuvveti (Tensile adhesion strength after freeze-thaw cycles)	≥ 0,5 N /mm²
Kayma (Slip)	≤ 0,5 mm
Açıkta durma zamanı:Yapışma mukavemeti(20 dakika sonra) (Open Time :Tensile adhesion strength(after not less than 20 minutes)	≥ 0,5 N /mm²