

MasterCrete[®] 285 Thix (Albaria[®] Struttura)

Puzolanic Lime Based, Repair Mortar Designed for Historical Masonry Buildings

Material Description

MasterCrete[®] 285 Thix is a high-strength, thixotropic repair mortar based on pozzolanic lime and natural graded aggregates, developed specifically for the restoration of historical masonry structures. It is a factory-produced masonry mortar that is completely cement-free and designed to provide excellent workability, adhesion, and full compatibility with traditional materials.

Areas of Application

- Repair and strengthening of masonry walls
- Repair and strengthening of arches and vaults
- Repair of wall and plaster surfaces
- Embedding of carbon rods into masonry joints
- Repair and strengthening of masonry foundations
- As a repair mortar for floor repairs or thick-layer applications when mixed with aggregate

Features and Benefits

- Cement-free composition
- High mechanical strength
- Excellent adhesion to substrate
- Low content of water-soluble salts
- Easy to prepare and apply
- Breathable; high water vapor permeability
- Low capillary water absorption
- High resistance to efflorescence

Processing Method

(A) Surface Preparation

The repair or plastering surfaces of historical masonry structures must be solid, dust-free, and clean. Remove all materials that may weaken adhesion such as oil, grease, or rust. Before applying MasterCrete[®] 285 Thix, moisten the surface to improve bonding and setting. If active water leakage exists, it should be stopped with a suitable plugging mortar and properly drained. No free water should remain on the surface before application.

Technical Properties

Structure of the Material	Pozzolanic lime and specially graded natural aggregates	
Water Vapour Permeability EN 1745	$\mu < 35$	WK
Water-Borne Salts UNI 11087	Electrical Conductivity $< 80 \mu S \cdot CM^{-1}$ $SO_4 < \%1$ $Na^+ < \%0,05$ $K^+ < \%0,05$	
Capillary Water Absorption UNI EN 1015/18	$0,2 \text{ kg} \cdot \text{m}^{-2} \cdot \text{min}^{-0,5}$	
Compressive Strength UNI EN 1015/11	$15-20 \text{ N/mm}^2$	
Modulus of Elasticity UNI EN 13412	$16,000 \text{ N/mm}^2$	
Application Temperature	$+5^{\circ}C + 40^{\circ}C$	

Typical values are obtained from the test results of 4x4x16 mortar prism in 23°C and 50% relative humidity conditions. High temperatures shortens the curing and working time, lower temperatures extends the durations.

Part of

MASTER[®]
>>BUILDERS
SOLUTIONS

Group



MasterCrete® 285 Thix (Albaria® Struttura)

Puzolanic Lime Based, Repair Mortar Designed for Historical Masonry Buildings

(B) Mixing

Pour the required amount of clean water into a mixing container. Gradually add MasterCrete® 285 Thix while mixing for about 4 minutes using a mechanical mixer at 400–600 rpm until a homogeneous and lump-free mixture is obtained. Let the mixture rest for about 4 minutes, then remix for 30 seconds before use.

Mixing Ratio

MasterCrete® 285 Thix	1 kg Powder	20 kg Bag
Water Quantity	0,15-0,17 liter	3,0-3,4 liter
Mixed Density	2,07-2,10 kg/liter	

(C) Processing

Apply the prepared mortar with a trowel at a thickness between 1–5 cm. After the mortar has lost its surface water, lightly sprinkle with water and finish with a steel or wooden trowel. For multi-layer applications, apply each layer only after the previous one has hardened. Each layer should not exceed 5 cm in thickness, and the previous layer should be moistened before applying the next one. For thick applications or screed-type repairs, add 30–35% by weight of clean, washed aggregate (5–20 mm). Depending on the desired consistency, the amount of water may be increased by 10–15%. On large exposed surfaces, especially in hot, dry, or windy conditions, protect the surface for 24–48 hours after application using wet burlap or gentle water curing to prevent rapid evaporation.

Consumption

Approximately **17.0 kg/m²** of dry product is required for a **1 cm** thick layer.

Points to Consider

- Do not apply when ambient or substrate temperature is below +5 °C or above +40 °C.

- During curing, the temperature of the environment and substrate must not fall below the permitted minimum.
- Protect outdoor applications for **24–48 hours** after application from direct sunlight, wind, rain, and frost.

Cleaning of Tools

Clean tools and equipment with water immediately after use. Once hardened, MasterCrete® 285 Thix can only be removed mechanically.

Packaging

20 kg polyethylene-reinforced kraft bag.

Shelf Life

12 months from the production date under appropriate storage conditions. Opened package should be tightly sealed and used within one week.

Storage

Store unopened bags in a cool, dry place, protected from frost. For short-term storage, stack a maximum of **3 pallets** and follow the **first in–first out (FIFO)** principle. For long-term storage, do not stack pallets.

Health and Safety

Standard precautions for handling chemical products should be followed. Wash hands thoroughly during breaks and after work. Do not eat, drink, or smoke during application. Refer to the **Safety Data Sheet (SDS)** for detailed safety and handling information. Product and packaging disposal must comply with local regulations; responsibility lies with the end user.

Part of

MASTER®
>>BUILDERS
SOLUTIONS

Group



MasterCrete® 285 Thix (Albaria® Struttura)

Puzolanik Lime Based, Repair Mortar Designed for Historical Masonry Buildings

Disclaimer

The information in this technical document is based on current scientific and practical knowledge. **MBT Teknik Yapı Kimyasalları Sanayi ve Ticaret A.Ş.** is responsible only for the quality of the product. The company cannot be held liable for results arising from improper use or applications outside the written recommendations. This technical data sheet remains valid until replaced by a newer version.

Contact

MBT Teknik Yapı Kimyasalları San. ve Tic. A.Ş.
Eyüp Sultan Mah. Sekmen Cad. Hayy 1000A No:26/8
Sancaktepe, İstanbul
Tel: 0216 561 35 45 www.mbt-tech.tr

CE	
2184	
MBT TEKNİK YAPI KİMYASALLARI SAN. VE TİC. A.Ş.	
Eyüp Sultan Mah. Sekmen Cad. HAYY 1000A No:26 K:5 D:8, 34885 Sancaktepe, İstanbul, Türkiye	
25	
DOP NO: 2108003	
2184-CPR-0491	
MasterCrete® 285 Thix (Albaria® Struttura)	
TS EN 998-2 G - Genel Kullanım Tasarlanmış Harç <i>General Purpose Designed Mortar</i> Kâgir Harcı - Özellikler - Bölüm 2: Kâgir Harcı <i>Specification for mortar for masonry - Part 2: Masonry mortar</i> Puzolanik Kireç Esaslı, Tarihi Yapı Onarım Harcı <i>Pozzolanic Lime Based Historical Building Repair Mortar</i>	
Basınç Dayanımı Compressive Strength	M15 Sınıf/Class
Kuru Yığın Yoğunluğu Dry Bulk Density	1800 kg/m ³
Bağ Dayanımı Bond Strength	> 0,15 N/mm ²
Klorür İçeriği Chloride ion Content	≤ 0,1%
Su absorpsiyonu Water absorption	< 0,5 kg/m ² vh
Su buhan geçirgenliği Water vapour permeability	15/35 µ
Isi iletkenlik Thermal conductivity	0,83 W/(m.K)
Yangına karşı tepki Reaction to fire	A1
Tehlikeli maddeler (Dangerous substances)	Madde 5.4.9'a uygun(Comply with clause 5.4.9)

Part of

MASTER®
»BUILDERS
SOLUTIONS

Group

