

Polyap[®] Y (MasterCrete[®] WS 700)

Adhesive for Heat Insulation Sheets

Material Description

Polyap[®] Y is a polymer-modified, cement-based, ready-to-use adhesive designed for bonding polystyrene heat insulation boards.

Complies with TS 13566

Areas of Application

Used as an adhesive for bonding thermal insulation boards in exterior insulation systems.

Characteristics and Benefits

- Excellent adhesion.
- Easy to prepare and apply.
- Extended working time.
- Resistant to freeze-thaw cycles.


Processing Method

(A) Preparation of Substrate

The application surface should be solid, load-bearing, clean, dust-free, and level. It must be completely free from any substances that may reduce adhesion, such as oil, grease, rust, or paraffin residues, and no loose particles should remain on the surface. Irregular surfaces with a depth of 5–20 mm should be repaired with **MBT Tech** repair mortars at least two days before application. If the substrate temperature exceeds +30°C, the surface should be slightly dampened before applying the adhesive.

(B) Mixing

The required amount of clean water is poured into a mixing container using a measuring tool. Polyap[®] Y powder is slowly added to the water and mixed with a mechanical mixer operating at 400–600 RPM for 3–5 minutes until a homogeneous and lump-free mixture is obtained. After allowing the mixture to rest for approximately 3–5 minutes, it should be remixed for 30 seconds before application.

Technical Properties		
Structure of the Material	Mineral fillers, synthetic additives and special cement	
Color	Gray	WK
Tensile Adhesion Strength (TS-EN 1348)		
from Concrete (TS-EN 1015-12)	≥0.50 N/mm ² (28 days)	
from Polystyrene (TS-EN 13494)	≥0.08 N/mm ² (28 days)	
Application Thickness	Min. 3 mm Max. 8 mm	
Application Substrate Temperature	+5°C to +25°C	
Service Temperature	-20°C to +80°C	
Maturation Time	3-5 minutes	
Working Time	1 hour	
Water Absorption (EN 12808-5)	Max. 5 g	
Flexural Strength	Min. 2 N/mm ²	
Compressive Strength	Min. 6 N/mm ²	

The above values are given for +23°C and 50% relative humidity. High temperatures shorten the times, while low temperatures extend them.

Part of

MASTER[®]
BUILDERS
SOLUTIONS

Group



Polyap[®] Y (MasterCrete[®] WS 700)

Adhesive for Heat Insulation Sheets

Mixing Ratio

Polyap [®] Y	Mixing Water Amount	Density of Mixture
For 1 kg powder	~0.25 liter	~1.63 kg/L
For 25 kg bag	~6.25 liters	

(C) Processing

The adhesive is applied along the edges of the thermal insulation boards as a continuous strip and as spots at the center areas using a mortar trowel.

The adhesive should cover at least 40% of the board surface. The boards are pressed and adjusted until the desired level and evenness are achieved. Depending on ambient temperature, once Polyap[®] Y has sufficiently set, the boards must be mechanically fixed to the surface using suitable anchors. During installation, the adhesive must not be allowed to dry or form a film on the surface of the boards. On very smooth substrates, Polyap[®] Y may be applied using a 10×10 mm notched trowel to ensure full coverage.

Consumption

Approximately 1.30 kg/m² of powder product is required for a 1 mm thick layer.

Points to Consider

- After the thermal insulation boards are bonded to the wall with Polyap[®] Y, they must be mechanically fixed to the surface using suitable anchors.
- During the application of Polyap[®] Y, if the ambient or substrate temperature is below +5°C or above +30°C, the work should be postponed until suitable conditions are achieved. Application should also be avoided in very hot, rainy, or windy weather.
- In exterior applications, the coated surface must be protected from direct sunlight, wind, frost, and rain for the first 24 hours after application.
- Under no circumstances should water or fresh material be added to a mixture that has already begun to set.

Cleaning of Tools

All tools and equipment should be cleaned with water immediately after use. Once Polyap[®] Y has hardened, it can only be removed from the surface mechanically.

Packaging

Supplied in 25 kg polyethylene-reinforced kraft bags.

Shelf Life

12 months when stored under the recommended conditions in unopened packaging. Opened bags should be tightly resealed and used within one week.

Storage

Store in its unopened original packaging in a cool, dry place protected from frost. For short-term storage, a maximum of three pallets may be stacked on top of each other, and delivery should follow the first-in, first-out principle. For long-term storage, pallets must not be stacked.

Health and Safety

During the application, a protective protective clothing, gloves, goggles, and mask which comply with the Occupational Health and Safety Rules should be used. Due to the irritation effect of the uncured materials, the mixture should not come into contact with skin and eyes; in case of a contact, the affected area should be washed with plenty of water and soap; in case of swallowing, a physician should be consulted immediately. No food or beverages should be brought to the application area. The product should be stored and kept out of reach of children. For detailed information please consult the Material Safety Data Sheet.

Disclaimer

The technical information given in this publication is based on the present state of our best scientific and practical knowledge. MBT Teknik Yapı Kimyasalları Sanayi ve Ticaret

Part of

MASTER[®]
»BUILDERS
SOLUTIONS

Group



Polyap[®] Y (MasterCrete[®] WS 700)

Adhesive for Heat Insulation Sheets

A.Ş. is only responsible for the quality of the product, **MBT Teknik Yapı Kimyasalları Sanayi ve Ticaret A.Ş.** is not responsible for results that may occur because the product is used other than advised and/or out of instructions regarding the place and the method of use. This technical form is valid only till a new version is implemented and nullifies the old ones.

Contact

MBT Teknik Yapı Kimyasalları San. ve Tic. A.Ş.
Eyüp Sultan Mah. Sekmen Cad. Hayy 1000A No:26/8
Sancaktepe, İstanbul
Tel: 0216 561 35 45 www.mbt-tech.tr

<div style="border: 1px solid black; width: 60px; height: 60px; margin: 0 auto; display: flex; align-items: center; justify-content: center; font-size: 40px; font-weight: bold; margin: 0 auto;">G</div> <p style="margin: 5px 0 0 0;">TSE</p>	
<p>MBT TEKNİK YAPI KİMYASALLARI SAN. VE TİC. A.Ş. Eyüp Sultan Mah. Sekmen Cad. HAYY 1000A No:26 K:5 D:8, 34885 Sancaktepe, İstanbul, Türkiye</p>	
Fabrika <i>Plant</i>	Ferizliob Mah. 10 Cad. No:2/1 Ferizli/Sakarya
Yıl <i>Year</i>	25
GBY No <i>Certificate Number</i>	2601001
Belge No <i>Certificate Number</i>	0415413-TSE-02/01
Standart No <i>Standard No</i>	TS 13566
Ürün Tipi <i>Product Type</i>	Polyap® Y Isı Yalıtım Levhası İçin Çimento Esaslı Yapıştırıcılar <i>Cement Based Adhesives For Thermal Insulating Board</i>
Taze Harcın Boşluklu Birim Hacim Kütleleri <i>Bulk Density of Fresh Mortar</i>	≥ 1000 mm ³
Elek. Analizi <i>Sieve Analysis</i>	1 mm elek. en çok %1 <i>Maximum %1 on 1 mm sieve</i>
Eğilme Dayanımı <i>Flexural Strength</i>	≥ 2 N/mm ²
Basınç Dayanımı <i>Compressive Strength</i>	≥ 6 N/mm ²
Alt Tabakaya Yapışma Kuvveti <i>Adhesion Strength to Substrate</i>	≥ 0,5 N/mm ²
Isı Yalıtım Levhasına Yapışma Kuvveti <i>Adhesion Strength to Thermal Insulating Board</i>	≥ 0,08 N/mm ²
Su emime <i>Water Absorption</i>	≤ 5 g

Part of

MASTER[®]
BUILDERS
SOLUTIONS

Group

