

MasterPozzolith 452

Non-chloride water-reducing admixture

Material Description

MasterPozzolith 452 is a ready to use liquid admixture formulated to improve the performance of concrete in both the plastic and hardened states. **MasterPozzolith 452** is a non-retarding, water reducing, strength enhancing admixture which does not contain added chloride.

Areas of Application

- All types of concrete where a non-chloride water reducing admixture is required.
- Improving the performance of pumped concrete, shotcrete and conventionally placed concrete
- Improving the performance of plain, reinforced, precast or standard weight concrete
- Concrete subject to chloride ion constraints such as in coastal environments
- Use in architectural concrete
- Concrete placed on galvanised steel floor and roof systems which are left in place

Characteristics and Benefits

MasterPozzolith 452 admixture aids in the production of concrete with these special qualities:

In the plastic state:

- Superior finishing characteristics for slab work and off-form surfaces
- Normal setting characteristics under cool conditions allowing earlier finishing of slabs
- Reduced segregation particularly in lean mixes and high slump concrete
- Improved workability
- Improved pumpability
- Reduced water content for a given workability

In the hardened concrete:

- No added chlorides, conforms to the most stringent chloride ion limits including AS3600 concrete structures code, will not initiate or promote the corrosion of reinforcing steel
- Increased strength - compressive, flexural and bond (concrete to steel)
- Superior finished appearance
- Increased density and durability
- Reduced permeability - improved watertightness
- Reduced cracking

Quantity to Use

MasterPozzolith 452 has a typical dose range of 250 – 400mls/100kg of total cementitious material & is normally used at a dose rate of 300mls per 100kg of cementitious material depending on the composition of the basic ingredients of the concrete and ambient conditions. **MasterPozzolith 452** can be used in summer at 400 to 500mLs per 100kg of cementitious material resulting in increased water reduction. The correct dosage rate in each instance should be determined by correctly conducted trials under the supervision of a Master Builders Solutions Technical Sales Representative.

Compatibility

MasterPozzolith 452 can be used with air entraining agents and other Master Builders Solutions admixtures, however Master Builders Solutions would recommend that evaluation trials be carried out to achieve optimum performance. During trials & concrete production, all admixtures should be dispensed separately and added separately to initial batching water to ensure complete distribution throughout the mix. **MasterPozzolith 452** can also be used in mix designs including fly ash, slag and silica fume.

Packaging

MasterPozzolith 452 is supplied in bulk, 1000 litre pallecons and 20 litre pails.



MasterPozzolith 452

Non-chloride water-reducing admixture

Storage & Shelf Life

If MasterPozzolith 452 has frozen, thaw at 2°C or above and completely reconstitute by mild mechanical agitation. Do not use pressurised air for agitation.

Precautions

For the full health and safety hazard information and how to safely handle and use this product, make sure that you obtain a copy of the Safety Data Sheet (SDS) from our office or website.

Disclaimer

MasterPozzolith-452-ANZ-V3-0723

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this MB Solutions Australia Pty Ltd publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use and for ensuring that the application and use of the product is in accordance with the manufacturer's guidelines and recommendations.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by MB Solutions Australia Pty Ltd either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not MB Solutions Australia Pty Ltd, are responsible for carrying out procedures appropriate to a specific application.

MB Solutions Australia Pty Ltd

ABN 69 634 934 419
 Unit 102, 2 Burbank Place
 Norwest NSW 2153

Freecall: 1300 227 300

www.master-builders-solutions.com/en-au

MB Solutions New Zealand Ltd

45C William Pickering Drive
 Albany, Auckland
 New Zealand

Phone: +64 9 414 7233

Emergency Advice:

1300 954 583 within Australia (24hr)
 0800 001 607 within New Zealand

