

MasterRoc[®] MSL 345

Spray Applied Waterproofing Membrane for Tunnel Concrete Composite Shell Linings

Material Description

MasterRoc[®] MSL 345 is an EVA polymer based sprayable membrane for the waterproofing of underground concrete structures. It is spray applied in a sandwich structure between two sprayed concrete / cast concrete layers, creating a double bonded composite shell lining. It is flexible and has very high bond strength properties on both sides of the membrane. It is an effective alternative to conventional waterproofing sheet membranes.

As a double bonded system, this provides excellent water tightness, preventing the development of water migration on both sides of the membrane.

As with all spray applied membranes, it is not possible to seal against water ingress through the substrate. In such cases, a drainage system or local water management using drainage pipes should be used in combination with MasterRoc[®] MSL 345. However, it can be applied to damp substrate (if there is no running water).

Areas of Application

- Particularly well suited for underground structures with complex profiles and geometry such as stations, escape and access tunnels, utility caverns, cross passages and tunnel intersections

- Suitable for all types of tunnel designs
- Enables tunnel design with composite shell lining to reduce excavation cross section and lining thickness, and is especially suited to tunnel rehabilitations

Characteristics and Benefits

- Fast curing
- Easy to use, only addition of water needed
- Application by spraying with simple equipment
- Elasticity 80% to 140% depending on temperature
- No toxic components
- No classification needed for transport
- Available in 2 colors if specification is requiring a 2-coat application otherwise applied as a 1 coat system

Consumption

Consumption depends on the surface roughness but is typically between 3 and 6 kg per m². For more information, please refer to the Method Statement.

Compatibility

MasterRoc[®] MSL 345 can be applied onto all types of concrete, if the surface is clean and without loose

Technical Properties

Form	Powder
Color	Light beige or orange
Water Pressure Resistance (max)	15 bar
Bulk Density (20°C)	590 g/l ± 100 g/l
Application Thickness	3 to 6 mm
Application Temperature	+5°C to +40°C
Failure Stress (at +20°C, at 28 days)	1.5 to 3.5 MPa
Failure Strain (at +20°C, at 28 days)	> 100%
Bond Strength to Concrete (28 days)	1.2 ± 0.2 MPa
Shore Hardness (28 days)	80 ±5
Flammability (in accordance with DIN 4102-B2)	Self-extinguishing

MasterRoc® MSL 345

Spray Applied Waterproofing Membrane for Tunnel Concrete Composite Shell Linings

particles. Sprayed concrete and cast concrete may be placed against the membrane surface once it has cured. Fiber reinforced sprayed concrete can be used on both sides of the membrane. It is also compatible with traditional waterproofing methods, enabling interface solutions with other systems (good bond to most sheet membranes and steel).

Equipment

MasterRoc® MSL 345 is applied by the dry spraying method using readily available dry spraying equipment like the Reed "Sove" pump.

- Rotor allowing low output (e.g., 18 pocket feedbowl)
- Rotor dust collector
- Spraying nozzle DIA 32 mm (plastic tip with collar/conical) with minimum 16-hole water ring (18 holes are recommended)
- Spraying hose DIA 32 mm

Curing

The speed of curing depends on weather conditions on site (humidity, wind conditions and temperature). We recommend not exposing the membrane to air temperatures outside the range of +5°C and +40°C for a minimum of 5 days following application, and cyclic variations should not exceed 10°C within this range.

Packaging

MasterRoc® MSL 345 is available in 15 kg plastic bags, (60 bags on a pallet).

Storage and Shelf Life

MasterRoc® MSL 345 has a shelf life of 12 months if stored in original, unopened bags between +5 °C to +40°C. The product must be kept out of direct sunlight. The storage area must be kept dry.

Health and Safety

The use of gloves, eye protection and safety clothes are recommended. Any physical contact (e.g., skin or eyes) with the product should be avoided. If contact with skin occurs, wash thoroughly using soap and water. In case of eye contact, rinse thoroughly with an eyebath filled with water and seek medical advice. The cured product is harmless and inert.

Uncured products should not enter the local drainage system. Spillage must be collected using absorbent materials such as sawdust and/or sand and disposed of in accordance with local regulations.

For further information please refer to the Safety Data Sheet or contact your local Master Builders Solutions representative.

Disclaimer

The technical information given in this publication is based on the present state of our best scientific and practical knowledge. **MBT Teknik Yapı Kimyasalları Sanayi ve Ticaret A.Ş.** is only responsible for the quality of the product **MBT Teknik Yapı Kimyasalları Sanayi ve Ticaret A.Ş.** is not responsible for results that may occur because the product is used other than advised and/or out of instructions regarding the place and the method of use. This technical form is valid only till a new version is implemented and nullifies the old ones.

Contact

MBT Teknik Yapı Kimyasalları San. ve Tic. A.Ş.
Eyüp Sultan Mah. Sekmen Cad. Hayy 1000A
No:26/8 Sancaktepe, İstanbul
Tel: 0216 561 35 45 www.mbt-tech.tr
master-builders-solutions.com/en-tr