

MasterRoc MG 03

High strength flowable grout for long strand cables and strata binding

Material Description

MasterRoc MG 03 is a shrinkage compensated, highly flowable precision grout for placement of cable bolts and strata binding. The product exhibits high early and ultimate strengths and can be used in underground mine and civil tunnel applications.

Areas of Application

MasterRoc MG 03 is particularly suitable as a grout used for the encapsulation of roof bolts and cable anchors where the "bottom up" grouting method is preferred.

Characteristics & Benefits

- High ultimate strengths ensure the permanence and safety of critical installations
- High flow characteristics enables the full encapsulation of bolts through narrow grout tubes and penetration of fine fissures
- Extended working time enabling easier clean-up of pumps and hoses
- Shrinkage compensated for greater bond strength to surrounding borehole & strata
- High bond to steel

Performance Characteristics

Grout strength development is dependent on the amount of mixing water, ambient temperature, age and curing. Typical rates of strength development of 20kg of **MasterRoc MG 03** grout with 6.0 litres of water are shown below:

Compressive Strength – Typical results
 (AS1478.2 Appendix A, restrained 50mm cubes at 23°C)

1 day	7 days	28 days
35 MPa	65 MPa	90 MPa

Mixing Equipment

For best results mix using a high mechanical shear or paddle mixer. Any grout mixer/pump must have accurate water dosage facilities.

Mixing

MasterRoc MG 03 is supplied ready to use, requiring only the addition of potable water. Do not use hardened or lumpy grout caused by torn or water damaged bags.

Actual amount of water will depend on the desired consistency of the grout required and the grout pump available. As a guide, use 5.5 - 8 litres per 20kg bag.

Do not use excess water. Discard any grout that has been left in excess of 60 minutes. Do not re-temper.

Placement

Master Builders Solutions provide a range of support services which can include operator training, underground audits and stock control assistance. Each service package can be developed to suit individual site requirements.

It is strongly recommended that a review with fully trained and qualified Master Builders Solutions personnel is conducted prior to placement of **MasterRoc MG 03**.

Cleaning

Systematic cleaning of the pump, grout and lines with clean water is essential. This should be done immediately after completion of grouting operations. If delays occur greater than 1 hour, the batched grout should be discarded and the unit cleaned out.

Estimating Data

20kg of **MasterRoc MG 03** grout with 6.5 litres of water will yield approximately 13.0 litres (0.013m³).



MasterRoc MG 03

High strength flowable grout for long strand cables and strata binding

Packaging

MasterRoc MG 03 is packaged in 20kg moisture resistant paper bags.

Storage & Shelf Life

Pallets should be stored in a dry, covered place. MasterRoc MG 03 has a shelf life of 12 months.

Precautions

For the full health and safety hazard information and how to safely handle and use this product, make sure that you obtain a copy of the Safety Data Sheet (SDS) from our office or website.

Disclaimer

MasterRoc-MG03 -ANZ-V6-0723

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this MB Solutions Australia Pty Ltd publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use and for ensuring that the application and use of the product is in accordance with the manufacturer's guidelines and recommendations.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by MB Solutions Australia Pty Ltd either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not MB Solutions Australia Pty Ltd, are responsible for carrying out procedures appropriate to a specific application.

MB Solutions Australia Pty Ltd

ABN 69 634 934 419
 11 Stanton Road
 Seven Hills NSW 2147

Freecall: 1300 227 300

www.master-builders-solutions.com/en-au

MB Solutions New Zealand Ltd

45C William Pickering Drive
 Albany, Auckland
 New Zealand

Phone: +64 9 414 7233

Emergency Advice:

1300 954 583 within Australia (24hr)
 0800 001 607 within New Zealand

