

# MasterKure CC 100WB

Wax emulsion curing compound

## Material Description

**MasterKure CC 100WB** (clear or white) is a water based wax emulsion compound for curing fresh moist plain concrete. It forms a flexible film which prevents concrete drying out during the critical early stages of hydration thus ensuring satisfactory curing of the concrete. **MasterKure CC 100WB** meets the requirements of AS 3799-1998, "Specification for Liquid Membrane-Forming Curing Compounds for Concrete" when applied at the recommended application rate.

## Areas of Application

- All types of external concrete paving
- Applications where damp curing is impracticable
- Concrete road pavements to prevent base course bonding to top course
- Use as a bond breaker in lift slab construction

**MasterKure CC 100WB** (clear or white) is not recommended for application when subsequent renders, toppings or coatings are to be applied. **MasterKure CC 100WB** white is not recommended for coloured concrete finishes.

## Characteristics and Benefits

- Efficient curing of concrete, assists the development of strength, abrasion resistance and durability and reduces the likelihood of cracking or dusting at the surface
- Easy to use, quick means of curing which requires no further attention, eliminates the problems of messy water curing
- Safe to use, **MasterKure CC 100WB** is non-flammable, non-corrosive, non-toxic and non-staining, less hazardous than some other methods of curing
- Economical

## Typical Performance Data

AS 3799-1998 specification requires that curing compounds achieve a minimum efficiency index of 90% in 72 hours. Water retention efficiency conducted on **MasterKure CC 100WB** provided the following results.

Application Rate	5m <sup>2</sup> /litre
Efficiency Index	>90%
Drying Time:	Approximately 3 hours at 23°C

NOTE: The data shown is based on controlled laboratory tests. Reasonable variations from the results can be expected in practice due to field conditions.

## Properties

The concrete shall be cured with **MasterKure CC 100WB** applied as soon as the concrete has set sufficiently so as not to be marred by the application. Formed surfaces shall be cured as soon as the forms have been stripped. Preparation of surfaces, quantities used, application procedures and installation precautions shall be followed in strict compliance with Master Builders Solutions recommendations and directions.

## Application

### When to use

**MasterKure CC 100WB** should be applied in one coat immediately after the final finishing operation as soon as the surface has hardened sufficiently to prevent marring. The surface should be damp but with no free water on it. Delaying the application of **MasterKure CC 100WB** until the next day will allow considerable loss of moisture, reducing the effectiveness of the curing membrane.

### How to use

Apply uniformly and thinly so as to form a continuous film. **MasterKure CC 100WB** is applied using a wide short nap roller, brush, or low-pressure spray. Do not dilute. **MasterKure CC 100WB** is supplied in clear or white pigmented to reduce heat absorption by the concrete.

## Estimating Data

Actual coverage depends on the texture and porosity of the surface. The recommended application rate is 5m<sup>2</sup>/litre.



# MasterKure CC 100WB

Wax emulsion curing compound

## Cleaning

Clean equipment immediately after use with hot water. If allowed to dry, use MasterSeal 955 to clean up.

## Packaging

MasterKure CC 100WB is available in clear or white pigmented in pails of 20 litre, drums, 200 litre drums and 1000 litre pallecons.

## Storage & Shelf Life

MasterKure CC 100WB has a shelf life of approximately 12 months if stored in its original sealed container at moderate temperatures. Do not allow to freeze. Avoid as far as possible storage in direct sunlight and avoid long-term exposure to high temperatures.

## Precautions

For the full health and safety hazard information and how to safely handle and use this product, make sure that you obtain a copy of the Safety Data Sheet (SDS) from our office or website.

## Disclaimer

MasterKure-CC100WB-ANZ-V5-0623

### STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this MB Solutions Australia Pty Ltd publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use and for ensuring that the application and use of the product is in accordance with the manufacturer's guidelines and recommendations.

### NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by MB Solutions Australia Pty Ltd either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not MB Solutions Australia Pty Ltd, are responsible for carrying out procedures appropriate to a specific application.

### MB Solutions Australia Pty Ltd

ABN 69 634 934 419  
 Unit 102, 2 Burbank Place  
 Norwest NSW 2153

Freecall: 1300 227 300

[www.master-builders-solutions.com/en-au](http://www.master-builders-solutions.com/en-au)

### MB Solutions New Zealand Ltd

45C William Pickering Drive  
 Albany, Auckland  
 New Zealand

Phone: +64 9 414 7233

### Emergency Advice:

1300 954 583 within Australia (24hr)  
 0800 001 607 within New Zealand

