

MasterGlenium SKY 8885

New generation High Range Water Reducing admixture with SURETEC (super retaining technology) for premix and precast applications

Material Description

MasterGlenium SKY 8885 is a uniquely formulated latest generation high range water reducer with super retention technology. **MasterGlenium SKY 8885** contains poly carboxylate ether polymers combined with SURETEC polymers ready-mixed & precast concrete where slump retention, improved rheology, durability, high early & ultimate strength are required. The degree of slump retention will depend on ambient temperature, mix design and dose rate. A unique combination of dispersion and steric hindrance effect makes **MasterGlenium SKY 8885** is a high dispersant super plasticizer ideal for the ready-mixed and precast concrete industries. The ability to work with low water/cement ratios and still obtain extended slump retention allows for the manufacture of high quality concrete.

MasterGlenium SKY 8885 is free of added chlorides, and is compatible with all cements meeting recognized international standards. **MasterGlenium SKY 8885** meets the requirements for High Range Water Reducers according to AS 1478.1-2000, Type HWR.

Areas of Application

- Slump retaining and super slump retaining concrete
- Faster mixing logistics during large jobs
- High flowability concrete
- Concrete that requires improved surface finish
- Ready-mixed and premixed concrete
- High Strength / Ultra High strength concrete
- Super Workable Concrete / Self Consolidating Concrete
- High Performance Concrete with high durability
- Pumped concrete
- Piling mixes
- Pre-stressed and post tensioned concrete
- High quality precast products – ie beams, columns etc

Characteristics and Benefits

- High range water reduction - high early and ultimate strengths.
- Low permeability, high durability concrete.

- High flowability - ease of placing and compaction. No segregation.
- Superior slump retention (> 3 hours), i.e. no re-tempering / ease of delivery to point of placement can be achieved with the addition of the Master Builders Solutions admixture MasterSure 1008.
- Low shrinkage and creep - improve dimensional stability. Reduced risk of cracks.
- Good cohesion - ease of pumping.
- Good rheology - excellent surface finish.
- Suitable for use with super workable concrete / self-consolidating concrete.
- Excellent bleed profile ensuring the highest concrete quality.
- High elastic modulus - superior load bearing capacity.
- Ideal for supplementary cementitious materials for achieving "Green Star" rating.

Properties

Colour	Brown to dark brown
Specific Gravity	1.09 ± 0.02
pH	6.0 ± 1.0

Application

MasterGlenium SKY 8885 is a ready-to-use liquid admixture, that can be added to the concrete mix as a separate component with the initial batch water, however optimal water reduction and workability is obtained if **MasterGlenium SKY 8885** is poured into the concrete mix right after the addition of the first 50 -70% of the mixing water. Avoid adding the admixture to the dry aggregates /cement. A separate dispenser and feed line must be used.

Dosage

Dosage of **MasterGlenium SKY 8885** depends on the mix design, ambient conditions, degree of water reduction, workability and workability retention required. **MasterGlenium SKY 8885** is normally dispensed at a rate of 300ml to 600ml / 100 kg of cementitious material. An increase in dosage may give slight slump enlargement which comes down in 30 – 60 minutes after mixing.



MasterGlenium SKY 8885

New generation High Range Water Reducing admixture with SURETEC (super retaining technology) for premix and precast applications

Other dosages from 700 – 1000 ml / 100 kg cementitious material may also be used depending on the specific mix design (like HPC, SWC, SCC, HSC, UHSC, etc.) and working conditions but should be trialed first to verify performance.

The optimum dosage rate in each instance should be determined by correctly conducted trials using materials and conditions of use under the supervision of a Master Builders Solutins Technical Sales Representative.

Compatibility

MasterGlenium SKY 8885 is not compatible with admixtures containing β -naphthalene sulphonate condensates (BNS).

MasterGlenium SKY 8885 can be used in combination with other Master Builders Solutions admixtures to achieve cost effective customized performance, like addition with other PCE based MasterPolyheed mid-range water reducers, MasterGlenium range of high range water reducers. It can be used effectively in combination with non-chloride (MasterSet AC 534) and chloride based (MasterSet AC 102) accelerators to reduce set times and bleed rates for winter concreting.

Each admixture should be dispensed separately into the mix to ensure complete distribution throughout the mix. It is imperative that any combination must be tested in controlled laboratory or field trials to ensure the combination will meet the desired performance parameters before proceeding to actual project mixes.

Care should be taken when used in conjunction with an air entrainer (AEA) as there may be a synergistic effect increasing the air content of the final mix above that desired. Trial mixes should be made with job materials and all admixtures or combinations to determine the optimum dosages required and to verify concrete performance for a specified job requirement before commencing supply. **MasterGlenium SKY 8885** should not be used in conjunction with other admixtures unless specific test information is available or advised by a Master Builders Solutions Technical Sales Representative.

Packaging

MasterGlenium SKY 8885 is available in 1000 litre palecons and bulk delivery.

Storage & Shelf Life

Keep only in the original container in a cool, dry, well-ventilated place away from ignition sources, heat or flame. Store protected against freezing. Protect from direct sunlight. Storage stability: Storage temperature: 5 - 45 °C Protect from temperatures below: 5 °C The packed product is destroyed at low temperatures or by frost. Protect from temperatures above: 45 °C The packed product must be protected against exceeding the indicated temperature. **MasterGlenium SKY 8885** has a shelf life of 12 months when stored as recommended above.

MasterGlenium SKY 8885 should be recirculated before use.

Precautions

For the full health and safety hazard information and how to safely handle and use this product, make sure that you obtain a copy of the Safety Data Sheet (SDS) from our office or website.



MasterGlenium SKY 8885

New generation High Range Water Reducing admixture with SURETEC (super retaining technology) for precast and precast applications

Disclaimer

MasterGlenium-SKY8885-ANZ-V6-0623

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this MB Solutions Australia Pty Ltd publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use and for ensuring that the application and use of the product is in accordance with the manufacturer's guidelines and recommendations.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by MB Solutions Australia Pty Ltd either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not MB Solutions Australia Pty Ltd, are responsible for carrying out procedures appropriate to a specific application.

MB Solutions Australia Pty Ltd

ABN 69 634 934 419
 Unit 102, 2 Burbank Place
 Norwest NSW 2153

Freecall: 1300 227 300

www.master-builders-solutions.com/en-au

MB Solutions New Zealand Ltd

45C William Pickering Drive
 Albany, Auckland
 New Zealand

Phone: +64 9 414 7233

Emergency Advice:

1300 954 583 within Australia (24hr)
 0800 001 607 within New Zealand

