

MasterRoc MF 50I

High performance plasticising and water-reducing admixture for mine backfill mixes

Material Description

MasterRoc MF 50I admixture is a liquid, water-reducing admixture used to enhance backfill properties.

Areas of Application

MasterRoc MF 50I is recommended for use in:

- Paste fill
- High density fill
- Cemented rockfill
- Hydraulic fill

Characteristics & Benefits

- Reduces the water content of back fill materials leading to higher in-situ strengths
- Improves slump and flow properties
- Increases in-place strength at all ages
- Normal setting time and rate of hardening
- Reduces pumping and distribution pressures
- Mix optimization and/or cost savings by binder reduction (cement/slag cement/fly ash)
- Enhances workability (rheological properties) in all types of backfills, requiring less water
- Reduces segregation of high density slurries
- Reduces permeability and shrinkage in hardened fill
- Potentially reduces cycle time and increases production

Dosage

The dosage range for MasterRoc MF 50I admixture may be affected by the total cementitious materials content of the mixture and by the particle size distribution of the backfill material.

The normal dosage range of the admixture is 300-900ml/tonne of backfill.

Application

MasterRoc MF 50I can be dispensed directly into the water or the entire wetted out mix. MasterRoc MF 50I admixture should not be dispensed directly onto the dry binder or with other admixtures.

Compatibility

When used in conjunction with other admixtures must be dispensed separately into the mix. The admixture is not typically chemically reactive with most backfill materials. Testing is recommended prior to use.

Do not use MasterRoc MF 50I admixture with admixtures containing beta-naphthalene-sulfonate. Erratic behaviours in slump, slump flow and pumpability may be experienced.

For directions on the proper evaluation of MasterRoc MF 50I admixture in specific backfill applications, contact your local Master Builders Solutions Technical Sales Representative.

Packaging

MasterRoc MF 50I is available in 1 000 litre pallecons.

Storage & Shelf Life

Keep away from heat. Store protected against freezing. Do not keep the container sealed. Formation of CO₂ and build-up of pressure possible.

MasterRoc MF 50I has a minimum shelf life of 12 months. Please contact your local Master Builders Solutions Technical Sales Representative regarding suitability for use and dosage recommendations if shelf life of MasterRoc MF 50I admixture has been exceeded.

Precautions

For the full health and safety hazard information and how to safely handle and use this product, make sure that you obtain a copy of the Safety Data Sheet (SDS) from our office or website.



MasterRoc MF 50I

High performance plasticising and water-reducing admixture for mine backfill mixes

Disclaimer

MasterRoc-MF50I -ANZ-V6-0723

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this MB Solutions Australia Pty Ltd publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use and for ensuring that the application and use of the product is in accordance with the manufacturer's guidelines and recommendations.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by MB Solutions Australia Pty Ltd either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not MB Solutions Australia Pty Ltd, are responsible for carrying out procedures appropriate to a specific application.

MB Solutions Australia Pty Ltd

ABN 69 634 934 419
 11 Stanton Road
 Seven Hills NSW 2147

Freecall: 1300 227 300

www.master-builders-solutions.com/en-au

MB Solutions New Zealand Ltd

45C William Pickering Drive
 Albany, Auckland
 New Zealand

Phone: +64 9 414 7233

Emergency Advice:

1300 954 583 within Australia (24hr)
 0800 001 607 within New Zealand

