

MasterRoc[®] MF 90I

High performance plasticizing and water-reducing admixture for cementitious mine backfill

Description

MasterRoc MF 90I is a liquid, water-reducing admixture used to enhance backfill properties.

Applications

Recommended for use in:

- Cemented paste fill
- Cemented high density hydraulic fill
- Cemented rock fill
- Cemented aggregate fill

Features

- Reduced water content of backfill materials for given slump
- Improves slump and flow properties (rheological properties)
- Increases in-place strength at all ages
- Normal setting time and hardening rate
- Reduces pumping and distribution pressures
- Quick wetting effect, high efficiency mixing, and higher flow rates
- Can be added at a higher than recommended dosage to achieve extended time of setting

Benefits

- Mix optimization and/or cost savings by reduction of binders (cement, slag cement, fly ash)
- Enhanced workability of the backfill materials, requiring less water
- Higher in-situ strengths of the backfill materials
- Potentially reduces the cycle time and increases production
- Reduces permeability and shrinkage in hardened backfill materials

Guidelines for Use

Dosage: The dosage range of MasterRoc MF 90I admixture may be affected by the total cementitious materials content of the mixture and by the particle size distribution of the backfill materials. The normal dosage range of MasterRoc MF 90I admixture is 6 – 18 fl oz/ton (200 - 600 mL/tonne) of total backfill. Dosage rates outside the recommended range may be used after conducting trial mixes.

Application Procedure: MasterRoc MF 90I admixture can be dispensed directly into the water or to the entire wetted-out mix. However, MasterRoc MF 90I admixture should not be dispensed directly onto the dry binder or with other admixtures.

Product Notes

Corrosivity: Non-Chloride, Non-Corrosive: MasterRoc MF 90I admixture does not contain intentionally added calcium chloride or chloride-based ingredients.

Compatibility: When used in conjunction with other admixtures, each admixture must be dispensed separately into the mix. The admixture is not typically chemically reactive with most backfill materials. Testing is recommended prior to use.

Do not use MasterRoc MF 90I admixture with admixtures containing beta-naphthalene-sulfonate. Erratic behaviors in slump, slump flow and pumpability may be experienced.

For directions on the proper evaluation of MasterRoc MF 90I admixture in specific backfill applications, contact your local sales representative.

Storage and Handling

Storage Temperature: MasterRoc MF 90I admixture should be stored at temperatures above 40 °F (5 °C), and be kept away from excessive heat and direct sunlight. If MasterRoc MF 90I admixture freezes, thaw at temperatures above 35 °F (2 °C), and reconstitute completely by mild agitation. Do not use pressurized air for agitation.

Shelf Life: MasterRoc MF 90I admixture has a minimum shelf life of 12 months when properly stored. Please contact your local sales representative regarding suitability for use and dosage recommendations if the shelf life of MasterRoc MF 90I admixture has been exceeded.

Packaging

MasterRoc MF 90I admixture is supplied in IBC totes, or by bulk delivery upon request.

Related Documents

Safety Data Sheet: MasterRoc MF 90I admixture

Additional Information

For additional information on MasterRoc MF 90I admixture, or its use in developing a backfill mixture with special performance characteristics, please contact your local sales representative.

Master Builders Solutions creates technologies for the construction industry inspiring people to build better. We are active in ~40 countries and operate 35 production sites with over 1,600 employees. We develop, produce, and market high-quality chemical admixtures, as well as adjacent core technologies, to master the challenges of today and support a decarbonized future. Our people are pivotal and pair leading technologies and a strong brand heritage to surpass our customers' expectations and drive continuous value creation.

Limited Warranty Notice

Master Builders Solutions Admixtures US, LLC ("Master Builders Solutions") warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. MASTER BUILDERS SOLUTIONS MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders Solutions. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. MASTER BUILDERS SOLUTIONS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders Solutions' present knowledge and experience. However, Master Builders Solutions assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders Solutions reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.