

03 37 13

Shotcrete

31 32 33

**Shotcrete Soil Slope
Stabilization**

31 33 33

**Shotcrete Rock Slope
Stabilization**

31 74 19

Shotcrete Tunnel Lining

MASTER[®]
» BUILDERS
SOLUTIONS

MasterRoc[®] SA 192

Alkali-Free, Liquid, High-Performance Set Accelerator for Sprayed Concrete

Description

MasterRoc SA 192 admixture is a high-performance, alkali-free shotcrete accelerator for use in the wet-mix spraying process. It is a liquid additive whose dosage can be adjusted to achieve the desired setting and hardening times.

Applications

Recommended for use in:

- Temporary and permanent ground support in tunneling and mining operations
- Slope stabilization
- Also suitable for the acceleration of cementitious grouts, such as annulus grout used in TBM tunneling, cement grout used in injections, and cellular concrete used in backfill operations

Features

- Ability to construct thick sprayed concrete linings during one construction sequence
- Enables early-age strength development, good long-term strength and enhanced durability
- Unique and advanced formulation
- Fast setting

Benefits

- Easy storage with no remixing or recirculation needed
- Allows rapid work progress
- Very low dust generation during application and hence, better working environment and improved worker safety
- Low rebound (when concrete is sprayed at the correct nozzle angle and distance)

Performance Characteristics

Technical data

Form	Liquid
Color	Clear
Density at 68 °F (20 °C)	11 ± 0.25 lb/gal (1.33 ± 0.03 g/mL)
pH	2.7 ± 0.5
Viscosity*	60 ± 20 cP (mPa.s)
Thermal stability	40 °F to 105 °F (5 °C to 40 °C)

* Brookfield, at 68 °F (20 °C). Viscosity is dependent on degree of product agitation and temperature.



Guidelines for Use

Dosage: The dosage of MasterRoc SA 192 admixture depends on the water-cementitious materials ratio (w/cm), reactivity of the cement, and temperature of concrete, ambient air and the substrate. The dosage also depends on the required layer thickness, setting time and early-strength requirements.

The dosage of MasterRoc SA 192 admixture normally ranges from 3% to 10% of the binder weight. Overdosing (> 12%) may result in decreased final strength.

Concrete mixtures:

- MasterRoc SA 192 admixture can be sensitive to the type of cement. It is recommended that ordinary portland cement be used in the wet-sprayed concrete mixtures, as against blended or sulfate-resistant cements that could result in slower setting times. However, MasterRoc SA 192 admixture also works well with blended cements and in mixtures containing fly ash or slag cement. It is strongly recommended that preliminary tests be conducted with the cements planned for use in the project to verify the setting time and the 24-hour strength of the concrete mixtures.

- When MasterRoc SA 192 admixture is used for wet mix spraying, the w/cm should be below 0.5, and preferably below 0.45. When targeting extremely high-early strength, the w/cm should be below 0.40. In general, a low w/cm provides faster setting, higher early strength, better durability and lower accelerator dosage. Low w/cm also enables thicker layers of concrete to be sprayed overhead.

Dispensing and Mixing: MasterRoc SA 192 admixture is added at the nozzle. It is essential to have a constant and accurate dosage of MasterRoc SA 192 admixture into the concrete stream in order to ensure the quality of sprayed concrete.

Works very well with:

- Mono pumps (stator & rotor pumps)
- Peristaltic pumps

Do not use with:

- Piston pumps
- Any pump with ball and seat valves
- Pressure tanks
- Gear pumps

Do not use a filter on the suction hose as this causes obstructions. Preferably draw the material from the bottom of the container.

Application procedure: The substrate should be clean and free from loose particles, and preferably damp.

Cleaning of dosing pump: After the use of MasterRoc SA 192 admixture, the dosing pump and other parts of the system must be thoroughly cleaned with plenty of water. Failure to do this promotes blockages in the dosing system. Make sure that all operators involved in testing and application are fully informed.

Product Notes

Compatibility:

MasterRoc SA 192 admixture can be interchanged with most of Master Builders Solutions' alkali-free accelerators. For advice, please contact your local sales representative.

Do not mix or interchange MasterRoc SA 192 admixture with any type of accelerator produced by another manufacturer, as this can cause immediate clogging of dosing pumps and hoses.

Storage and Handling

Storage: MasterRoc SA 192 admixture should be stored at a temperature range of 40 °F to 95 °F (5 °C to 35 °C). The optimum temperature of storage and performance is 68 °F (20 °C). Please contact your local sales representative prior to the use of any product that is frozen.

MasterRoc SA 192 admixture must be kept in closed containers made of plastic, glass fiber, or stainless steel. Do not store in steel containers as the pH can cause corrosion which might affect the performance of the product. Storage containers must be tightly closed at all times to avoid contact with air.

Performance testing should always be carried out prior to use of MasterRoc SA 192 admixture after prolonged storage.

Shelf Life: If stored in tightly closed original containers under the above conditions, MasterRoc SA 192 admixture has a shelf life of 12 months. Storing at temperatures above 60 °F (15 °C) will prolong the shelf life further.

Safety: Avoid eye and skin contact and wear rubber gloves and safety glasses. If contact occurs, rinse with plenty of water. In case of eye contact, seek medical advice immediately. For further information, refer to the Safety Data Sheet for MasterRoc SA 192 admixture.

Packaging

MasterRoc SA 192 admixture is supplied in IBC totes, drums, and by bulk delivery upon request.

Related Documents

Safety Data Sheet: MasterRoc SA 192 admixture

Additional Information

For additional information on MasterRoc SA 192 admixture, please contact your local sales representative.

Master Builders Solutions creates technologies for the construction industry inspiring people to build better. We are active in ~40 countries and operate 35 production sites with over 1,600 employees. We develop, produce, and market high-quality chemical admixtures, as well as adjacent core technologies, to master the challenges of today and support a decarbonized future. Our people are pivotal and pair leading technologies and a strong brand heritage to surpass our customers' expectations and drive continuous value creation.

Limited Warranty Notice

Master Builders Solutions Admixtures US, LLC ("Master Builders Solutions") warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. MASTER BUILDERS SOLUTIONS MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders Solutions. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. MASTER BUILDERS SOLUTIONS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders Solutions' present knowledge and experience. However, Master Builders Solutions assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders Solutions reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.