

# MasterJoint™ TC 269

Polyurethane Based, Two Components, UV Resistant, Protective Top Coat

## Material Description

**MasterJoint™ TC 269** is two components, solvent containing, UV resistant, polyurethane based top coating.

## Areas of Application

It is used as topcoat polyurethane UV coating for **MasterJoint™** insulation systems.

## Characteristics and Benefits

- Two components, easy to apply.
- Elastic.
- Resistant to UV and air conditions.
- Has a higher aliphatic polyurethane prepolymer structure.

## Processing Method

### (A) Preparation of Substrate

The surface of the coating on which **MasterJoint™ TC 269** is to be applied should be free of dust, dirt, oil and other adhesion impairing contaminants. The application should be carried out within the recoating interval of the coating. Contact our Technical Services for the application on old coating.

## (B) Processing

### Primer Application

**MasterJoint™ TC 269** has two components. Prior to use, the product is mixed with an epoxy/polyurethane padded drill at 300-400 rpm for 3-4 minutes without causing air bubbles.

Make sure that the temperature of the material is between +15°C-+25°C prior to mixing. **MasterJoint™ TC 269** should be applied to the surface using a squeegee (wiper) or a roller. For applications with rollers, the surface should be well raked to minimize streaks. Thick application may cause foaming.


## Consumption

0.15-0,20 kg/m<sup>2</sup>

## Point to Consider

- Avoid applications under excessive heat or wind and/or when the ambient and/or substrate temperature is below +10°C or above +30°C.
- The materials to be used at the appropriate temperatures should be brought in and stored in the application area 1-2 days prior to the application and enabled to adjust the ambient conditions.

## Technical Properties

Structure of the Material	Polyurethane	
Color	RAL Colours	
Solid Matter Ratio	%64	
Density	1,27 kg/lt	LX
Viscosity (4 mm DIN cup)	90 s	
Application Temperature	+10°C +30°C	
Pot Life	1 hours	
Recoatibility Time	Min. 24 hours - max. 3 days	
Full Curing Time	5 days	

The above figures are valid for 23°C and intended as a guide only and should not be used as a basis for specifications.

Part of

**MASTER®**  
**BUILDERS**  
SOLUTIONS

Group



# MasterJoint™ TC 269

Polyurethane Based, Two Components, UV Resistant, Protective Top Coat

- In extremely cold conditions, heaters should be used to increase the ambience and the workability of the product, the packages should be preconditioned to +20°C - +25°C to become ready to use.
- Epoxy and polyurethane based floor coatings should be applied by approved applicators.
- The reaction and workability times of resin-based systems depend on the ambience and substrate temperatures as well as the relative humidity. Under lower temperatures, the chemical reaction times are prolonged, and this increases the pot life, coating interval and the working time. In addition to this, consumption is increased as the viscosity increases. High temperatures ignite stronger chemical reactions, and the above-mentioned times decrease accordingly. For the material to be cured properly, the ambient and the substrate temperatures should not fall below the specified limits. After the application, the material should be protected from direct contact with water for 24 hours minimum. Within this period, contact with water may cause a surface carbonation and/ or tackiness; both of which will cause the coating to lose its characteristics. In such cases, the overall coating should be removed from the floor and renewed.
- Permissible relative humidity is 80% max. during application.
- **MasterJoint™ TC 269** is two components set. No solvent etc. should be added during application.
- The empty packages should be consolidated and disposed of properly in order to prevent reusing the packages.

## Cleaning of Tools

Used tools and equipment must be cleaned carefully with an appropriate solvent. Once cured **MasterJoint™ TC 269** can only be removed by mechanical means.

## Packaging

9,9 kg set  
Part A: 8,3 kg metal pail  
Part B: 1,6 kg metal pail

## Shelf Life

The shelf life is 12 months from the date of production under suitable storage conditions. Opened packages should be stored under suitable storage conditions and used within 1 week.

## Storage

Must be stored in between +15 °C and +35 °C, unopened original packing, and in cool and dry environment protected from freezing. Delivery has to be according to first in first out system. In long-term storing, the palettes must not be stowed on top of each other.

## Health and Safety

It is dangerous to approach the application sites. During the application, protective apparel, protective gloves, goggles and masks which comply with the Occupational Health and Safety Rules should be used. Due to the irritation effect of the uncured materials, the mixture should not come into contact with skin and eyes; in case of contact, the affected area should be washed with plenty of water and soap; in case of swallowing, a physician should be consulted immediately. No food or beverages should be brought to the application area. The product should be stored and kept out of reach of children. For detailed information please consult the Material Safety Data Sheet.

# MasterJoint™ TC 269

Polyurethane Based, Two Components, UV Resistant, Protective Top Coat

## Disclaimer

The technical information given in this publication is based on the present state of our best scientific and practical knowledge. **MBT Teknik Yapı Kimyasalları Sanayi ve Ticaret A.Ş.** is only responsible for the quality of the product **MBT Teknik Yapı Kimyasalları Sanayi ve Ticaret A.Ş.** is not responsible for results that may occur because the product is used other than advised and/or out of instructions regarding the place and the method of use. This technical form is valid only till a new version is implemented and nullifies the old ones.

## Contact

MBT Teknik Yapı Kimyasalları San. ve Tic. A.Ş.  
Eyüp Sultan Mah. Sekmen Cad. Hayy 1000A  
No:26/8 Sancaktepe, İstanbul  
Tel: 0216 561 35 45 [www.mbt-tech.tr](http://www.mbt-tech.tr)

<b>CE</b>	
<b>MBT TEKNİK YAPI KİMYASALLARI SAN. VE TİC. A.Ş.</b>	
Eyüp Sultan Mah. Sekmen Cad. HAYY 1000A No:26 K:5 D:8, 34885 Sancaktepe, İstanbul, Türkiye	
25	
DOP NO 1103002	
EN 13813 SR-B1.5-AR0.5	
MasterJoint™ TC 269	
İç mekan kullanımına uygun reçine kaplama harcı Resin screed mortar for indoor use	
Aşınma Direnci Wear resistance	AR0,5
Bağ Dayanımı Bond strength	B1.5
Çarpmaya Direnç Impact resistance	≥ 6 Nm
Aşındırıcı maddelerin salınımı Release of corrosive substances	SR
Yangına Karşı Tepki Reaction To Fire	E <sub>1</sub>
Tehlikeli maddeler (Dangerous substances)	Güvenlik bilgi formu Safety data sheet

Part of

**MASTER®**  
**>>BUILDERS**  
SOLUTIONS

Group

