

Technical Data

Water absorption	ISO 10545/3 ASTM C373	0,23% 0,23%
Breaking strength	ISO 10545/4	40,6 N/mm ²
Grazing resistance	ISO 10545/11	resistant, no visible effect
Frost resistance	ISO 10545/12 ASTM C1026	resistant, no visible effect resistant, no visible effect
Resistance to thermal shock	ISO 10545/9 ASTM C484	resistant, no visible effect resistant, no visible effect
Chemical resistance	ISO 10545/13 ASTM C650	resistant, no visible effect not affected
Stain resistance	ISO 10545/14	5
Slip resistance	DIN 51130-04	R9
Dimensions	ISO 10545/2	compliant with standard
Length and width		± 0,6%
Thickness		± 5%
Straightness of sides		± 0,5%
Wedging		± 0,6%
Surface flatness		± 0,5%