

# MasterJet S FrontLit 510 B1 Magic

Item	Unit	Value	Test Method
Base Fabric	Denier	1000DX1000D	(High tenacity yarn) 100%PES
Construction	Weaving/inch	20x20	/
Weight of fabric	Gsm/m <sup>2</sup>	175±10	DIN53352 BS3424 Method5B
Weight of PVC	Gsm/m <sup>2</sup>	335±10	DIN53352 BS3424 Method5B
Total weight	Gsm/m <sup>2</sup>	510±20	DIN53352 BS3424 Method5A
Thickness	mm	0.40±0.02	DIN EN ISO 2286-3
Width	cm	Up to 510	/
Tensile Strength	N/5cm	Warp	2200
		Weft	1900
Tearing Strength	N	Warp	300
		Weft	250
Adhesion	N/5cm	80	DIN53357 BS3425 Method9B
Temperature Resistance	°C	-20 ~ 70	DIN53357 BS3425 Method10
Lacquering	None		
Flammability	B1		
Low cadmium & heavy metals	Reach Compliance		
Conclusions and announcements	<p>Declaration by Igepa: Please choose Igepa products suitably according to relative provisions or industrial standards. Igepa bears the responsibility for the specified technical and performance data on this page only. Igepa is not responsible for any other liability. (The technical data on this page is calculated on average, and ± 5% tolerance is acceptable).</p> <p>Remarks : 'G' represents Glossy surface, "M" represents Matte surface, Glossy or Matte could be made as requirements.</p>		