

## Prime PET Clear 175 UV

UV Curing – clear /transparant



### Technical Data

|                 |  |
|-----------------|--|
| Thickness:      | 175 µm based on ISO2286-3  |
| Tear Resistant: | 1.980 kg/cm <sup>2</sup> (LR), ASTM D 882<br>2.126 kg/cm <sup>2</sup> (QR), ASTM D 882 |
| Shrinkage:      | 1,38% (LR), ASTM D 1204<br>0,39% (QR), ASTM D 1204                                     |
| Front/Back:     | glossy   |
| Surface:        | Clear/Transparent  |
| Shelf life:     | 2 years when properly stored under 15° - 20°C  |

### General Information

- 100% Polyester Film
- PVC-free
- Printable with UV-curing inks
- Splashproof
- Dimensionally stable



## Prime PET Clear 175 UV

UV Curing – clear /transparant

### Areas of application

- Citylights and Light boxes
- Ideal for mobile spit protection walls (e.g. roll-ups) For clinics & hospitals, public institutions, Department stores, authorities, airports, petrol stations etc..
- Visor protection for helmets

### Advantages

- Good rigidity
- Highly tear resistant
- Very long lasting
- Ideal Product for mobile protective walls and visors
- Dimensionally stable
- Washable
- 100% PVC-free
- Recyclable

### Printing properties

- Printable with UV Curing inks

### Processing instructions

- It is necessary to dry the print completely before further processing, a drying time of 24 hours is recommended
- The surface must be dry, clean, absorbent and smooth
- The use of cotton gloves is recommended to avoid fingerprints.
- The optimal room climate during processing would be in between 15 ° - 35 ° C and a humidity of 40% - 65%