

WestRock
FoldKraft™
The natural choice when productivity matters.



If you're looking for an uncoated kraft paperboard solution that runs well and looks good, you've found it. WestRock FoldKraft™ is engineered for consistency and flatness to maximise equipment speed and minimise costly downtime. FoldKraft's market-leading smoothness delivers sharper images and excellent solid ink coverage. And, with the addition of PE coating, FoldKraft is ideal for Foodservice packaging where a grease and moisture barrier is critical. FoldKraft is the preferred choice for converters and brands, naturally.

Region

EMEA (Europe, the Middle East and Africa)

Packaging uses

- Bakery
- Drink Carriers
- Dry, Refrigerated & Frozen Food
- Filter Frames
- Foodservice
- Gift Boxes
- Home Goods
- Office Products
- Partitions
- Sporting Goods

Product Classification

- Uncoated
- Unbleached Kraft
- UUK Paperboard

What You Can Expect from Us

Productivity Maximise throughput and reduce costly equipment jams — highly consistent, lays very flat, and runs extremely clean on press with minimal fibre picking.

Printability A smooth surface for a cleaner look, sharper images and excellent solid ink coverage.

Strength and Integrity High tear strength and stiffness levels result in a strong and durable finished product that maintains its integrity in dry, refrigerated, and frozen environments.

Recycled Fibre Content Produced with up to 15% recycled fibre.

Additional Product Information

Sustainability Made with recycled fibre and is recyclable.

Chain of Custody 100% PEFC™ Certified - BV/CDC/0575784

Food Contact Meets multiple national requirements for food contact packaging, e.g., US, Canada, Germany and the EU. Contact your sales representative for information on specific markets and end uses. ISEGA Certificate available.

Quality Produced at an ISO 9001 certified facility.

Environmental and Safety Notices under US California Proposition 65 and the EU REACH regulation are not required.

Meets heavy metal limits of the US Model Toxics in Packaging rules and Article 11 of EU Directive 94/62/EC.



Grade Availability (EMEA) & Typical Properties

FoldKraft™

Grade Availability							Units	Method	
Nominal Basis Weight	264	283	317	352	381	420	gsm	T-410	
Caliper (pts)	0.015	0.016	0.018	0.020	0.022	0.024	inches	T-411	
Thickness	381	406	457	508	559	610	microns	T-411	
ZDT	35	35	35	35	35	35	psi	T-541	
Elmendorf Tear									
Dry	MD	400	430	505	565	610	650	gf	T-414
	CD	410	450	540	600	665	725	gf	T-414
Stiffness									
Taber 15°	MD	16.2	21.1	29.4	39.2	49.0	58.8	mNm	T-489
	CD	6.7	8.3	12.7	16.7	21.1	25.5	mNm	T-489
Smoothness									
Sheffield	250	250	250	250	250	280	mL/min	T-538	

Values are subject to change without notice.

LDPE Poly Configurations Available

Thickness

Mils (U.S.)	0.50	0.75
Microns	12.7	19.1

Basis Weight

lbs/MSF (U.S.)	2.4	3.6
gsm	11.7	17.6

Poly coating is available in P1S and P2S.
This product is Corona treated.

For more information, please contact your WestRock representative or visit our website at westrock.com.

The information contained in this Product Guide is accurate to the best of WestRock's knowledge and belief. It is intended, however, only as an introduction to the typical properties of the product. WestRock disclaims any guarantee or warranty with respect to the accuracy of this information or, based on this document, with respect to the suitability of the product for any particular use, including, but not limited to, the compliance of the product with laws, regulations, or standards. This information is subject to change without notice.

© 2018 WestRock Company. WestRock® and FoldKraft™ are trademarks of WestRock Company. All rights reserved worldwide.

