

Datasheet



AUFW00024 Feast Watson Slate & Pebble Sealer

Introduction


Part A

872 94658

Description and Image

Feast Watson Slate & Pebble Sealer is a tough clear, non yellowing coating that locks out moisture, protecting stone surfaces from weather and abrasion and mild solvents such as petrol, oil and kerosene. Slate & Pebble Sealer is suitable for interior and exterior application, and is ideal for use in bathrooms, foyers, driveways, steps, pathways and roof tiles (except glazed or semi-glazed tiles). Slate & Pebble Sealer gives a gloss finish that is easily re-coatable.

Caution Smooth surfaces may become slippery when wet.



Features and Benefits

- Non yellowing
- Clear film
- Acrylic resin
- Interior/ Exteroir
- Enhances natural beauty of slate
- Fast drying

Uses

Use Feast Watson Slate And Pebble Sealer on slate and exposed pebble aggregate. Ideal for protecting and binding aggregate back onto the cement surface.

Precautions and Limitations

Do not apply in temperatures under 10°C or above 35°C or when rain or heavy dew is expected within the coating dry time.

Performance Guide	
Weather For interior and exterior use	Heat Resistance Up to 120C.
Water Excellent	Abrasion Excellent

Typical Properties	
Gloss Level Satin	
Colour Clear	



Datasheet



Components 1		Number of Coats 2	
Toxicity Lead free.		V.O.C. Level < 715g/L	
Clean Up			
	ustion of contaminated application clo fore disposal. Do not scrunch up or pl	ths, immediately spread used application ace cloths on top of each other.	on cloths flat in a cool, well
Application Methods			
🕇 Brush 🔭 Roller	<u>L</u> Pad		
Application Conditions	Solids by Volume		
	16		
	Min	Max	Recommended
Wet Film Per Coat (microns)			100
Dry Film Per Coat (microns)			16
Recoat Time (min/hours)	2 Hours		
Theoretical Spread Rate (m²/L)		12	10
Typical Property Notes Coverage Slate: 10 - 12m2 per litre Pebble: 6 - 8m2 per litre Roof Tiles: 8 - 10m2 per litre			
Drying Time Drying times are given at 25°C and 5	50% relative humidity. Lower tempera	tures or higher humidity can lead to ext	ended drying times.
Light foot traffic 24 hours.			

Application Guide

Surface Preparation

Ensure surface is thoroughly clean and free from oil, grease, dirt and moss prior to application. Clean the surface with Feast Watson Floorclean as per the product instructions. For new concrete and aggregate pebbles allow the surface to cure for approximately 28 days then treat surface with a 10% solution (dilute) of Hydrochloric Acid. Apply Hydrochloric Acid using a brush or mop, allow the acid to remain on the surface for 15 minutes then flush off with clean water. Allow the surface to dry completely before applying Slate & Pebble Sealer.

Application Procedure and Equipment

Stir thoroughly before and during use with a broad flat stirrer to maintain a uniform solution Apply a minimum of two coats of Slate & Pebble Sealer using either a Feast Watson Floor Finish Applicator, brush, fine mohair or wool roller.

Maintenance

Monitor the surface for signs of loss of gloss or scratches. If an additional coat is required, clean using Floorclean. Apply one coat of Slate & Pebble Sealer as per application instructions.

Health and Safety



Datasheet



SDS Number

2607

SDS Link

https://go.lupinsys.com/duluxgroup/harms/public/materials/3c8bb9f

28239cf735c4e49d35e54ef4epublished/attachments api/e0288a8da0845ed33254573780d89724/s

earch api/87294658 FEAST WATSON SLATE AND PEBBLE SEALERAUS GHS.pdf

Using Safety Precautions

Risk

Highly Flammable. Harmful by inhalation and in contact with skin. Irritating to respiratory system and skin. Toxic to aquatic organisms. May cause long term adverse effects in the aquatic environment. Avoid contact with skin and eyes and breathing in vapour or spray mist. Wear overalls, impervious gloves and safety glasses. Use only in well ventilated areas. If inhalation risk exists wear organic vapour/particulate respirator. This paint is flammable, so eliminate any sources of ignition. Do not smoke. Do not empty into drains. Keep containers closed when not in use.

Please refer to SDS Link. In case of emergency, please call 1800 220 770.

Transport and Storage		
Pack A 872-94658		
Size:	Weight:	
20 Litres 10 Litres 4 Litres 1 Lit	17.9 Kg 9.0 Kg 3.6	6 Kg 895g
Please refer to the Safety Data S	heet for full safety, heal	Ith and trans

Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from www.duspecplus.com.au. Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.