

Feast Watson Spar Marine Varnish Gloss

AUDW1623

Part A	870 94644
---------------	-----------

Description

Feast Watson SPAR MARINE VARNISH is an extremely flexible spar varnish designed to withstand the rigors of sun, water and harsh outdoor treatment. Being flexible when fully cured allows SPAR MARINE VARNISH to bend and flex without cracking or splitting, making it perfect for functional timber such as yachts and tools. SPAR MARINE VARNISH is a clear, high gloss varnish with UV protection. SPAR MARINE VARNISH is ideal for all above-water-line marine applications as well as all exterior timber.

Note: SPAR MARINE VARNISH is NOT suitable for heavy wear surfaces (such as decks and walkways). For these areas use Feast Watson DECKING OIL or Feast Watson DECKING STAIN.

Features

Extremely flexible spar varnish.

Benefits

- Withstand the rigors of sun, water and harsh outdoor treatment.
- Flexes to prevent cracking.
- Water and UV resistant.

Uses

All above-water-line marine applications as well as all exterior timber.




Precautions And Limitations

Drying times are given at 25°C and 50% relative humidity. Lower temperatures or higher humidity can lead to extended drying times. Do not apply in temperatures under 10°C or above 35°C or when rain or heavy dew is expected within the coating dry time.

SPAR MARINE VARNISH is NOT suitable for heavy wear surfaces (such as decks and walkways). For these areas use Feast Watson DECKING OIL or Feast Watson DECKING STAIN.

Performance Guide

Weather	Exterior durable.	Salt	Unaffected by splash or spillage.
Heat Resistance	Up to 120C.	Water	Excellent.
Solvent	Suitable for dilute splash.	Acid	Suitable for dilute splash.
Alkali	Suitable for dilute splash.		

Typical Properties																											
Gloss Level	High gloss	Colour	Clear																								
Components	1	Number Of Coats	3																								
Toxicity	Lead free	V.O.C. Level	< 445g/L																								
Touch Dry	6 hours																										
Clean Up Description	Mineral turpentine To avoid spontaneous combustion of contaminated application cloths, immediately spread used application cloths flat in a cool, well ventilated area to dry completely before disposal. Do not scrunch up or place cloths on top of each other.																										
Application Method	 Air Spray  Brush  Roller																										
Application Conditions	<table border="0" style="width: 100%;"> <tr> <td style="text-align: center;">Solids By Volume</td> <td style="text-align: center;">45</td> <td></td> <td></td> </tr> <tr> <td></td> <td style="text-align: center;">Min</td> <td style="text-align: center;">Max</td> <td style="text-align: center;">Recommended</td> </tr> <tr> <td>Wet Film Per Coat (microns)</td> <td></td> <td></td> <td style="text-align: center;">100</td> </tr> <tr> <td>Dry Film Per Coat (microns)</td> <td></td> <td></td> <td style="text-align: center;">45</td> </tr> <tr> <td>Recoat Time (min)</td> <td style="text-align: center;">12 hours</td> <td></td> <td></td> </tr> <tr> <td>Theoretical Spread Rate (m²/L)</td> <td></td> <td style="text-align: center;">12</td> <td style="text-align: center;">10</td> </tr> </table>			Solids By Volume	45				Min	Max	Recommended	Wet Film Per Coat (microns)			100	Dry Film Per Coat (microns)			45	Recoat Time (min)	12 hours			Theoretical Spread Rate (m²/L)		12	10
Solids By Volume	45																										
	Min	Max	Recommended																								
Wet Film Per Coat (microns)			100																								
Dry Film Per Coat (microns)			45																								
Recoat Time (min)	12 hours																										
Theoretical Spread Rate (m²/L)		12	10																								
Typical Properties Notes	<p>COVERAGE Softwood: 8 - 10m² per litre. Hardwood: 10 - 12m² per litre.</p> <p>DRYING TIME Drying times are given at 25°C and 50% relative humidity. Lower temperatures or higher humidity can lead to extended drying .</p>																										

Application Guide	
Surface Preparation	<ul style="list-style-type: none"> ▪ New Timber Allow new timber to acclimatise in its final position for 4-6 weeks. Coat with Feast Watson TIMBER PRIMER to protect it from stains and warping during the acclimatisation period. Prepare exterior timber for coating with Feast Watson WOODCLEAN as per the instructions. Sand to a smooth surface and remove all sanding dust before coating. Weathered Timber Prepare exterior weathered or grey timber by cleaning thoroughly with WOODCLEAN as per the instructions. Sand to a smooth surface and remove all sanding dust before coating. Previously Coated Timber Previously coated surfaces need to be taken back to bare timber by sanding timber to a smooth surface. Remove all sanding dust before coating.
Application Procedure And Equipment	<ul style="list-style-type: none"> ▪ SPAR MARINE VARNISH should be stirred thoroughly before and during application with a flat blade stirrer taking care not to introduce bubbles. Apply SPAR MARINE VARNISH using a brush, roller or spray. If spraying SPAR MARINE VARNISH may be thinned by using 10% mineral turpentine. If applying by roller, use a short nap (5mm) mohair roller. Ensure edges and end grain are fully coated. Apply minimum three coats. Four or more coats may be applied for extra durability to withstand extreme exposure or when the coating has been thinned. Allow 12 hours drying between coats. Sand lightly between coats. The final coat should be applied within 30 hours of the previous coat to ensure timber is protected. MAINTENANCE Regularly monitor the surface for signs of colour loss or surface defects. When required,lightly sand the surface and remove dust. Recoat with additional coats of SPAR MARINE VARNISH as per application instructions.

Health And Safety			
MSDS Number	3787	Using Safety Precautions	Avoid contact with skin and eyes and breathing in vapour or spray mist. Wear overalls, impervious gloves and safety glasses. Use only in well ventilated areas. If inhalation risk exists wear organic vapour/particulate respirator. This paint is flammable, so eliminate any sources of ignition. Do not smoke. Do not empty into drains. Keep containers closed when not in use.
Health Effects	<p>Irritating to skin.</p> <p>FIRST AID: For advice, contact a Poisons Information Centre (Phone Australia 13 11 26; New Zealand 0800 764 766) or a doctor.</p> <p>SWALLOWED: If swallowed, do NOT induce vomiting. Give a glass of water. Seek medical assistance.</p> <p>EYE: Rinse with plenty of running water. Seek medical help if irritation occurs.</p> <p>SKIN: If skin contact occurs, remove contaminated clothing and wash skin thoroughly.</p> <p>INHALED: Remove from contaminated area.</p> <p>For further product information or advice regarding Safety and First Aid, telephone the Feast Watson Customer Service Department on FREECALL 1800 252 502.</p>	Flammability	This product is flammable.
Storage	Keep out of reach of children.	Disposal	Do not pour leftover paint down the drain. Unwanted paint should be brushed out on newspaper, allowed to dry and then disposed of via domestic waste collections. Empty paint containers should be left open in a well ventilated area to dry out. When dry, recycle the container via steel can recycling programs. Disposal of empty paint containers via domestic recycling programs may differ between local authorities. Check with your local council first.
In the case of emergency, please call 1800 033 111			

Transport And Storage			
Pack A	870 94644	Shipment Name	PAINTS
Size	500ml 1L 4L	Weight	0.45Kg 0.9Kg 3.6Kg
Flash Point	>23C	UN Number	1263
Dangerous Goods Class	3	Package Group	III

Disclaimer

Dulux, Selleys and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating/product systems.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating/product systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Selleys" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "Acratex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427