

AUFW00025 Feast Watson Mastertouch French Polish

Introduction

Part A
917 94665

Description and Image

Feast Watson French Polish is a shellac based spirit varnish for use on furniture where a deep patina is desired. It is ideal for enthusiasts and professionals who want to achieve a warm, high gloss French polished finish for fine timber furniture. It is an authentic finish for the restoration of antique furniture and French polished surfaces. French Polish is not suitable on table tops subject to high wear or liquid spills.

Features and Benefits

- Traditional finish
- Fast drying
- May be tinted with a spirit stain
- Perfect for restoring fine furniture
- 1 hour re-coat
- makes colour matching easier

Uses



Use Feast Watson French Polish on furniture and other timber articles where a deep patina polish is desired. Not suitable for table tops subject to high use, and wet areas.

Precautions and Limitations

Drying times are given at 25°C and 50% relative humidity. Lower temperatures or higher humidity can lead to extended drying times. Do not apply in temperatures under 10°C or above 35°C.

Performance Guide

Weather For interior use only	Heat Resistance Up to 120C. Premature yellowing and embrittlement will occur if subjected to continuous heat.
Water Poor.	Abrasion Moderate resistance to abrasion.

Typical Properties			
Gloss Level Gloss	Heat Thinner Methylated spirits		
Colour Amber tone			
Components 1	Number of Coats 4 +		
Toxicity Lead free. Dry film is non-toxic and conforms to AS1647, Part 3.	V.O.C. Level < 550g/L		
Touch Dry 30 minutes			
Clean Up  Thinner			
Clean Up Description Methylated spirits. To avoid spontaneous combustion of contaminated application cloths, soak application cloths in water or immediately spread used application cloths flat in a cool, well ventilated area to dry completely before disposal. Do not scrunch up or place cloths on top of each other.			
Application Methods  Brush French polish mop, rubber or a clean cloth pad			
Application Conditions	Solids by Volume <input type="text" value="24"/>		
Recoat Time (min/hours)	Min <input type="text" value="1 hour"/>	Max <input type="text"/>	Recommended <input type="text"/>
Typical Property Notes Drying time Drying times are given at 25oC and 50% relative humidity. Lower temperatures or higher humidity can lead to extended drying times. Sanding 24 hours. Full curing after 7 days.			

Application Guide

Surface Preparation

New Timber
Sand to a smooth surface and remove all sanding dust before coating. To achieve a super-smooth finish or if the timber grain is open or coarse, seal with Feast Watson Sanding Sealer and sand back as per the directions.

Previously Coated Timber
Previously varnished surfaces need to be sanded to a dull finish. Remove all sanding dust before coating. Previously French polished surfaces should be cleaned thoroughly with warm soapy water or wood turpentine.

Antique Restoration
Seek professional advice before commencing work on antiques.

Application Procedure and Equipment

Surfaces to be coated must be dry and free from all dirt, dust, grease, polish, wax and oil. Apply in dry conditions between 15-30C. Apply French Polish with a good quality soft bristled brush, French polish mop, rubber or a clean cloth pad. Apply three coats of French Polish allowing one hour dry time between coats. After the third coat allow 24 hours to dry. If a more durable and higher gloss coating is desired, further coats can be applied. Rub down the surface with very fine sand paper or 000 steel wool, then clean the surface and apply more coats as above. After every third coat allow 24 hours to dry and rub back before applying subsequent coats. When the desired finish is achieved, set aside for a week to allow the finish to develop hardness. After 7 days, the gloss can be reduced by cutting and polishing the finish with fine 0000 steel wool lubricated with Feast Watson Mastertouch Wax, then buffing with a clean cloth.

Staining
Apply Feast Watson Proofint following label directions prior to the application of French Polish. Alternatively, add 10% Proofint to tint French Polish.

Maintenance
Maintain the surface finish by regularly applying Feast Watson Mastertouch Polish or Feast Watson Mastertouch Wax. Avoid placing hot items on surfaces coated with French Polish. Quickly clean and dry liquid spills.

Health and Safety

SDS Number 14606801	SDS Link View SDS Link
-------------------------------	---

Using Safety Precautions
Avoid contact with eyes. Provide adequate ventilation. If using indoors keep windows and doors open during use and while drying. All potential sources of ignition (open flames, pilot lights etc) must be eliminated both in or near the work area. Do not smoke.

Please refer to SDS Link. In case of emergency, please call 1800 220 770.

Transport and Storage

Pack A
917-94665

Size:	Weight:
<input type="checkbox"/> 4 Litre <input type="checkbox"/> 1 Litre <input type="checkbox"/> 500ml <input type="checkbox"/> 250ml	<input type="checkbox"/> 3.2 Kg <input type="checkbox"/> 800g <input type="checkbox"/> 400g <input type="checkbox"/> 200g

Please refer to the Safety Data Sheet for full safety, health and transportation information.

Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from www.duspecplus.com.au. Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.