

Feast Watson Timber Primer

AUDW1621

Part A	870 94634
---------------	-----------

Description

Feast Watson TIMBER PRIMER is a clear, water repellent penetrating wood preserver ideal for priming new interior and exterior timber. It has mould resistant properties and is designed to stabilise timber to minimise twisting and warping. Timber may be varnished or painted 12 hours after applying TIMBER PRIMER. TIMBER PRIMER is ideal for use on all timbers such as pergolas, window frames, undersides of flooring or lining boards, flooring joists and verandahs.

Also known as FUNGISHIELD.

Note: TIMBER PRIMER should not be used under penetrating coatings such as Feast Watson WOOD SHIELD OIL, DECKING OIL or DECKING STAIN.

Features

Penetrating wood preserver.

Benefits

- For interior and exterior bare timber.
- Resists mould and decay.
- Minimise twisting and warping.

Uses





All timbers such as pergolas, window frames, undersides of flooring or lining boards, flooring joists and verandahs.

Precautions And Limitations

TIMBER PRIMER should not be used under penetrating coatings such as Feast Watson WOOD SHIELD OIL, DECKING OIL or DECKING STAIN. Drying times are given at 25°C and 50% relative humidity. Lower temperatures or higher humidity can lead to extended drying times. Do NOT apply in temperatures under 10°C or above 35°C or when rain or heavy dew is expected within the coating drying period.

Performance Guide

Weather	Interior and Exterior.	Salt	Good.
Heat Resistance	Up to 80C.	Water	Excellent.
Solvent	Poor.	Abrasion	Poor.
Acid	Poor.	Alkali	Poor.

Typical Properties																											
Colour	Clear	Components	1																								
Number Of Coats	1-2	Toxicity	Lead free																								
V.O.C. Level	< 705g/L	Touch Dry	8 hours																								
Clean Up Description	Mineral turpentine To avoid spontaneous combustion of contaminated application cloths, soak application cloths in water or immediately spread used application cloths flat in a cool, well ventilated area to dry completely before disposal. Do not scrunch up or place cloths on top of each other.																										
Application Method	 Air Spray  Airless Spray  Brush  Roller																										
Application Conditions	<table> <tr> <td>Solids By Volume</td><td>15</td><td></td><td></td></tr> <tr> <td></td><td>Min</td><td>Max</td><td>Recommended</td></tr> <tr> <td>Wet Film Per Coat (microns)</td><td></td><td></td><td>100</td></tr> <tr> <td>Dry Film Per Coat (microns)</td><td></td><td></td><td>15</td></tr> <tr> <td>Recoat Time (min)</td><td>12 hours</td><td></td><td></td></tr> <tr> <td>Theoretical Spread Rate (m²/L)</td><td>8</td><td>12</td><td>10</td></tr> </table>			Solids By Volume	15				Min	Max	Recommended	Wet Film Per Coat (microns)			100	Dry Film Per Coat (microns)			15	Recoat Time (min)	12 hours			Theoretical Spread Rate (m²/L)	8	12	10
Solids By Volume	15																										
	Min	Max	Recommended																								
Wet Film Per Coat (microns)			100																								
Dry Film Per Coat (microns)			15																								
Recoat Time (min)	12 hours																										
Theoretical Spread Rate (m²/L)	8	12	10																								
Typical Properties Notes	<p>COVERAGE Softwoods: 8 - 10m² per litre Hardwoods: 10 - 12m² per litre</p> <p>DRYING TIME Drying times are given at 25°C and 50% relative humidity. Lower temperatures or higher humidity can lead to extended drying times.</p>																										

Application Guide	
Surface Preparation	<ul style="list-style-type: none"> New Timber Sand to a smooth surface and remove all sanding dust before coating. Previously Coated Timber Previously varnished surfaces need to be sanded to bare timber. Remove all sanding dust before coating.
Application Procedure And Equipment	<ul style="list-style-type: none"> TIMBER PRIMER should be stirred thoroughly before and during application with a flat blade stirrer. Apply a flood coat using a brush, roller or spray. Ensure edges and end grain are fully coated. A second coat may be necessary for porous timbers. Additional coats can be applied wet-on-wet. Allow surface to dry for 12 hours before overcoating with desired finish. STAINING TIMBER PRIMER can be tinted with up to 10% Feast Watson PROOFTINT.

Health And Safety

MSDS Number	141833	Using Safety Precautions	Irritating to skin. May cause sensitisation by skin contact. Wear overalls, impervious gloves and safety glasses. Use only in well ventilated areas. If inhalation risk exists wear organic vapour/particulate respirator. Keep away from sources of heat or ignition. No smoking. Keep containers closed when not in use.
Health Effects	<p>May cause sensitisation by skin contact. May cause lung damage if swallowed.</p> <p>FIRST AID: For advice, contact a Poisons Information Centre (Phone Australia 13 11 26; New Zealand 0800 764 766) or a doctor.</p> <p>SWALLOWED: If swallowed, do NOT induce vomiting. Give a glass of water. Seek medical assistance.</p> <p>EYE: Rinse with plenty of running water. Seek medical help if irritation occurs.</p> <p>SKIN: If skin contact occurs, remove contaminated clothing and wash skin thoroughly with soap and water.</p> <p>INHALED: Remove from contaminated area. Apply artificial respiration if not breathing.</p> <p>For further product information or advice regarding Safety and First Aid, telephone the Feast Watson Customer Service Department on FREECALL 1800 252 502.</p>	Flammability	This product is flammable.
Protective Equipment	Wear overalls, impervious gloves and safety glasses.	Storage	Keep out of reach of children.
Disposal	Do not pour leftover product down the drain. Keep unwanted product in sealed containers for disposal via special chemical waste collections. Disposal of empty containers via domestic kerbside recycling programs may differ between local authorities. Check with your local council first.		

In the case of emergency, please call 1800 033 111

Transport And Storage

Pack A	870 94634	Shipment Name	PAINTS
Size 250ml 500ml 1L 4L 20L	Weight 0.38Kg 0.65Kg 1.0Kg 4.0Kg 18.8Kg		
Flash Point	>23C	UN Number	1263
Dangerous Goods Class	3	Package Group	III

Disclaimer

Dulux, Selleys and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating/product systems.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating/product systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Selleys" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "Acratex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427