

## TPO 45 mil Membrane

### APPLICABLE STANDARDS

UL Listed, FM Approved, Miami-Dade County Product Control Approved, State of Florida Approved, CRRC Rated, Title 24 Compliant\*, ENERGY STAR® Certified\*\*, ASTM D6878.

Physical Properties	ASTM Test Method	ASTM D6878 Minimum	EverGuard® Typical Test Data
1. Certain data is provided in MD (machine direction) x CMD (cross machine direction) format.			
2. Data is based upon typical product performance, and is subject to normal manufacturing tolerance and variance.			
Nominal Thickness	ASTM D751	0.039" (min.) (0.99 mm)	0.045" (1.14 mm)
Breaking Strength	ASTM D751 Grab Method	220 lbf/in. (38.5 kn/m)	375 lbf x 330 lbf (559 x 492 kg/m)
Factory Seam Strength	ASTM D751	66 lbf (98.34 kg/m)	115 lbf (171 kg/m) (membrane failure)
Elongation at Break	ASTM D751	15%	30%
Heat Aging	ASTM D573	90% Retention of Breaking Strength and Elongation at Break	100%
Tear Strength	ASTM D751 8" x 8" (203 x 203 mm) Sample	55 lbf (81.95 kg/m)	90 lbf x 120 lbf (134 x 179 kg/m)
Puncture Resistance	FTM 101C Method 2031	Not Established	>350 lbs. (159 kg)
Cold Brittleness	ASTM D2137	-40°C	-40°C
Permeance	ASTM E96	Not Established	0.08 Perms
Dimensional Change	ASTM D1204 @158°F (70°C), 6 hrs.	+/- 1%	0.2%
Water Absorption	ASTM D471 @158°F (70°C), 1 week	+/- 3.0% max.	0.7%
Hydrostatic Resistance	ASTM D751 Method D	Not Established	390 psi
Ozone Resistance	ASTM D1149	No visible deterioration @ 7 x magnification	No visible deterioration @ 7 x magnification
SRI (Solar Reflectance Index) Initial/Aged	N/A	N/A	94/81 83 Aged Title 24
Reflectivity (white) Initial/Aged	ASTM C1549	N/A	0.76/0.68
Emissivity (white) Initial/Aged	ASTM C1371	N/A	0.90/0.83
Weather Resistance	ASTM G155/D6878	10,080 KJ/(m <sup>2</sup> . nm) at 340 nm	>20,000 KJ/(m <sup>2</sup> . nm) at 340 nm
Heat Aging	ASTM D573	240°F (115°C) for 32 weeks	60 weeks
Thickness Above Scrim	ASTM D7635	Min 30% of Total Thickness	15.8 mil (Nominal)
<b>Guarantee</b>			
Up to 20 years			

\*ENERGY STAR® only valid in the USA

\*White Membrane Only

In view of innovation, the specifications are subject to change without any prior notice and in the event of such changes, BMI shall ensure that the new specifications are equivalent if not better.

### PRODUCT INFORMATION

	5' x 100'	6' x 100'	8' x 100'	10' x 100'	12' x 100'
Roll Size	(1.52 x 30.5 m) (500 sq. ft. [46.5 sq.m])	(1.83 x 30.5 m) (600 sq. ft. [55.74 sq.m])	(2.44 x 30.5 m) (800 sq. ft. [74.3 sq.m])	(3.05 x 30.5 m) (1,000 sq. ft. [92.9 sq.m])	(3.65 x 30.5 m) (1,200 sq. ft. [111.484 sq.m])
Roll Weight	128 lb. (58.1 kg)	153.6 lb. (69.7 kg)	204 lb. (93 kg)	256 lb. (116.1 kg)	307.2 lb. (139.3 kg)
Colors	White / Tan / Gray	White / Tan / Gray	White / Tan / Gray	White / Tan / Gray	White / Tan / Gray
Storage	Store rolls on their sides on pallets or shelving in a dry area.				
Safety Warning	Membrane rolls are heavy. Position and install by at least two people.				

Note: Membrane rolls shipped horizontally on pallets, stacked pyramid-style and banded.

**MONIER MALAYSIA SDN. BHD.** (19163-M)

Suite 12W.12th Floor, Wisma FGV, Jalan Raja Laut, 50350 Kuala Lumpur

T (+60) (3) 21760600 F (+60) (3) 26040335 Toll Free: 1800 88 0865

roofing-malaysia@bmigroup.com

[bmigroup.com/my](http://bmigroup.com/my)