

TROJAN° DATA SHEET MOTIVE OVERDRIVE™ AES 31

MODEL OverDrive™ AES 31

VOLTAGE 12

CAPACITY **102Ah @ 20Hr**MATERIAL **Polypropylene**

BATTERY VRLA AGM / Non-Spillable / Maintenance-Free

COLOR Maroon

WATERING No Watering Required





12 VOLT

PHYSICAL SPECIFICATIONS

BCI	MODEL NAME	TERMINAL TYPE	DIMENSIONS © INCHES (mm)			WEIGHT LBS. (kg)	HANDLES	INSTALLATION ORIENTATION
29	OVERDRIVE™ AES 31	MX/III	LENGTH	WIDTH	HEIGHT F	(- ()	Plastic Handle	Horizontal and Vertical
			12.80 (325)	6.81 (173)	9.37 (238)	69 (31)		

ELECTRICAL SPECIFICATIONS

VOLTAGE	CRANKING PE	RFORMANCE	CAPACITY A MINUTES	CAPACITY ^B AMP-HOURS (Ah)		ENERGY (kWh)	INTERNAL RESISTANCE (mΩ)	SHORT CIRCUIT CURRENT (amps)		
10	C.C.A. ^D @0°F	C.A. ^E @32°F	@ 25 Amps	5-Hr	10-Hr	20-Hr	100-Hr	100-Hr	4.00	2555
12	657	788	180	82	-	102	-	-	4.80	

CHARGING INSTRUCTIONS

CHARGER VOLTAGE SETTINGS (AT 77°F/25°C)							
SYSTEM VOLTAGE	12V	48V					
Maximum Charge Current (A)	50% of C ₂₀						
Absorption Voltage (2.40 V/cell)	14.40	28.80	43.20	57.60			
Float Voltage (2.25 V/cell)	13.50	27.00	40.50	54.00			

Do not install or charge batteries in a sealed or non-ventilated compartment. Constant under or overcharging will damage the battery and shorten its life as with any battery.

CHARGING TEMPERATURE COMPENSATION

ADD	SUBTRACT
0.005 volt per cell for every 1°C below 25°C 0.0028 volt per cell for every 1°F below 77°F	0.005 volt per cell for every 1°C above 25°C 0.0028 volt per cell for every 1°F above 77°F

OPERATIONAL DATA

OPERATING TEMPERATURE	SELF DISCHARGE
-40°F to 140°F (-40°C to $+60$ °C). At temperatures below 32°F (0°C) maintain a state of charge greater than 60%.	Less than 3% per month depending on storage temperature conditions

RECYCLE RESPONSIBLY









STATE OF CHARGE MEASURE OF OPEN-CIRCUIT VOLTAGE

PERCENTAGE CHARGE	CELL	12 VOLT	
100	2.14	12.84	
75	2.09	12.54	
50	2.04	12.24	
25	1.99	11.94	
0	1.94	11.64	


TROJAN 31-AES PERFORMANCE



PERCENT CAPACITY VS. TEMPERATURE




BATTERY DIMENSIONS (shown with DT)



0

SELF DISCHARGE VS. TIME



TERMINAL TYPE

15	M8	M8	6	DT	AUTOMOTIVE POST & STUD
		Battery Height with Terminal in Inches (mm) 8.69 (221) Torque Values in-Ib (Nm) Bolt: 85 – 90 (10 – 11)	2		Battery Height with Terminal in Inches (mm) 9.37 (238) Torque Values in-lb (Nm) Connected to Stud: 95 – 105 (11 – 12) Connected to AP: 50 – 70 (6 – 8) Bolt Size 5/16" – 18

- A. The number of minutes a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 V/cell. Capacities are
- The national of minutes a sate of year deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 Vicell. Capacities are based on peak performance.

 The amount of amp-hours (Ah) a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 Vicell. Capacities are based on peak performance.
- Dimensions may vary depending on type of handle or terminal. Batteries should be mounted with 0.5 inches (12.7 mm) spacing minimum. C.C.A. (Cold Cranking Amps) - the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 0°F (-18°C) at a voltage above 1.2 V/cell.
- E. C.A. (Cranking Amps) the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 32°F (0°C) at a voltage above 1.2
- CAL Clothaning Analysis are deschaled before an amperes which a reversible place of the control and a second at 32 Voicel. This is sometimes referred to as marine cranting amps @ 32°F or M.C.A. @ 32°F. Height taken from bottom of the battery to the highest point on the battery. Heights may vary depending on type of terminal. Terminal images are representative only.
- H. Batteries in storage should be charged when they decline to 75% State of Charge (SOC).
- Weight may vary.











Designed in compliance with applicable BCI, DIN, BS and IEC standards. Tested in compliance to BCI and IEC standards.

