

# MIRAFI H2Rxx

**MIRAFI® H2Rxx** is a multi-functional stabilization geotextile engineered specifically for road pavements and railway structures with mechanical stabilization and moisture management capabilities. The super high tenacity polypropylene yarns allow mobilization of tensile resistance for reinforcement benefits at low working strains of 2%. The proprietary moisture wicking yarns have the capability to move soil moisture and dissipate it sideways horizontally even under unsaturated soil conditions. The added wicking loops improve the fabric absorbency and provide assisted in-plane drainage in the machine direction. The highly texturized woven geotextile surface results in a product with superior frictional resistance to provide excellent soil bonding and confinement against the lateral spreading of gravels at the interface of the geotextile and the structural aggregate layer.

Properties		Test Standard	Unit	H2Rxx
<b>Mechanical</b>				
Tensile strength at 2% strain	MD	ISO 10319	kN/m	20
Tensile strength at 2% strain	CD	ISO 10319	kN/m	20
Tensile strength at 5% strain	MD	ISO 10319	kN/m	50
Tensile strength at 5% strain	CD	ISO 10319	kN/m	50
CBR puncture strength		ISO 12236	kN	9
Grab strength	MD	ASTM D4632	N	2000
Grab strength	CD	ASTM D4632	N	2000
Tear strength	MD	ASTM D4533	N	750
Tear strength	CD	ASTM D4533	N	750
UV resistance <sup>1</sup>		EN 12224	% retained	90
G rating <sup>2</sup>		Austrroads	-	7000
<b>Hydraulic</b>				
Pore size, O <sub>90</sub>		ISO 12956	mm	0.30
Water permeability, Q <sub>50</sub>		ISO 11058	l/m <sup>2</sup> /min	1500
<b>Moisture management</b>				
Normal lines of wicking loops per meter width				75
<b>Wicking loop absorbency</b>				
Time for 2µl water drop to contact angle ≤ 2°		ASTM D5946 <sup>3</sup>	s	0.3
<b>Fabric moisture movement</b>				
Vertical wet front movement @ 25 min	MD	ASTM C1559 <sup>3</sup>	mm	80
Vertical wet front movement @ 25 min	CD	ASTM C1559 <sup>3</sup>	mm	150
Horizontal wet front movement @ 300 min	MD	ASTM C1559 <sup>3</sup>	mm	500
Horizontal wet front movement @ 300 min	CD	ASTM C1559 <sup>3</sup>	mm	1900
<b>Form of supply</b>				
Roll width			m	4.5
Roll length			m	100

**NOTES :**

- (1) Mean of MD & CD
- (2) Based on external lab testing
- (3) Modified test method

**Solmax Geosynthetics Asia Sdn. Bhd.** (formerly known as TenCate Geosynthetics Asia Sdn Bhd)

199301009495 (264232-U)  
 14, Jalan Sementa 27/91, Seksyen 27,  
 40400 Shah Alam, Selangor Darul Ehsan, Malaysia  
 Tel: +60 3 5192 8568 | Fax: +60 3 5192 8575

infoasia@solmax.com



Solmax is not a design or engineering professional and has not performed any such design services to determine if Solmax's goods comply with any project plans or specifications, or with the application or use of Solmax's goods to any particular system, project, purpose, installation, or specification.

**MIRAFI®** is a registered trademark of Solmax in many countries of the world.

