

TECHNICAL DATA SHEET

LLDPE 1.00 mm Black Smooth

PROPERTY ₍₁₎	TEST METHOD	FREQUENCY	UNIT Metric	1012113
SPECIFICATIONS				
Thickness (min. avg.) Thickness (min.)	ASTM D5199 ASTM D5199	Every roll Every roll	mm mm	1.00 0.90
Resin Density Melt Index - 190°C/2.16 kg (max.)	ASTM D1505 ASTM D1238	One per batch One per batch	g/cc g/10 min	< 0.926 1.0
Density Carbon Black Content Carbon Black Dispersion OIT - Standard (min. avg.)	ASTM D792 ASTM D4218 ASTM D5596 ASTM D3895	Every 10 rolls Every 2 rolls Every 10 rolls One per batch	g/cm³ % Category min	≤ 0.939 2.0 - 3.0 Cat. 1 / Cat. 2 100
Tensile Properties (min. avg) (2) Strength at Break Elongation at Break 2% Modulus (max.)	ASTM D6693 ASTM D5323	Every 2 rolls Per formulation	kN/m % kN/m	29 800 420
Tear Resistance (min. avg.) Puncture Resistance (min. avg.)	ASTM D1004 ASTM D4833	Every 5 rolls Every 5 rolls	N N	100 275
Dimensional Stability Multi-Axial Tensile (min.) Oven Aging - % retained after 90 days	ASTM D1204 ASTM D5617 ASTM D5721	Certified Per formulation Per formulation	% %	± 2 30
OIT - Standard (min. avg.) HP-OIT (min. avg.) UV Resistance - % retained after 1,600 hr HP-OIT (min. avg.)	ASTM D3895 ASTM D5885 ASTM D7238 ASTM D5885	Per formulation	% % %	35 60 35
Low Temperature Brittleness	ASTM D3883 ASTM D746	Certified	°C	- 77
SUPPLY SPECIFICATIONS(Roll dimer	nsions may vary ±1%)			0.00
Roll Dimension - Width Roll Dimension - Length	<u>-</u>		m m	8.00 210.0
Area (Surface/Roll)	-		m²	1680.0

NOTES

- 1. Testing frequency based on standard roll dimensions and one batch is approximately 180,000 lbs (or one railcar).
- 2. Machine Direction (MD) and Cross Machine Direction (XMD or TD) average values should be on the basis of 5 specimens each direction.

Solmax is not a design professional and has not performed any design services to determine if Solmax's goods comply with any project plans or specifications, or with the application or use of Solmax's goods to any particular system, project, purpose, installation or specification.

SOLMAX.COM

31-May-2018

^{*} All values are nominal test results, except when specified as minimum or maximum.

^{*} The information contained herein is provided for reference purposes only and is not intended as a warranty or guarantee. Final determination of suitability for use contemplated is the sole responsibility of the user. SOLMAX assumes no liability in connection with the use of this information.