



<b>New Jersey</b>					
Dated 2019		Section 919.01		AASHTO M288	
Category		Woven (elongation < 50%)		Nonwoven (elongation > 50%)	
<b>Subsurface Drainage % fines</b>					
< 15%		Class 2	FW404	160N	
15% to 50%			FW700		
> 50%			FW700		
Stabilization		Class 1	600X	180N	
<b>Erosion Control Geotextile<sup>2,3</sup></b>					
< 15%		Class 1	FW404	180N	
15% to 50%			--		
> 50%			--		
< 15%		Class 2	FW404	160N	
15% to 50%			FW700		
> 50%			FW700		
Paving Geotextile				MPV500	

<sup>2</sup> For inlet filters, use Class 2 for woven monofilament geotextiles or Class 1 for all other types of geotextiles

<sup>3</sup> For inlet filter, Type 2 in addition to the AASHTO M288 requirements, ensure that the geotextile's burst strength is at least 650 # per square inch when tested according to ASTM D3786.

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

Copyright © 2015 Nicolon Corporation. All Rights Reserved