

# CROIXFIX

## PUNCTUAL CONCRETE SPACER

Spacer



Update on 01/07/2025

### Description

The CROIXFIX spacer is a waterproof concrete spacer made from high-strength concrete without fibers with a double loop wire or twice plastic clip.

This spacer is almost invisible when stripping formwork with the flat reduced support surface, star-shaped.

### Applies to

The CROIXFIX spacer:

- is easily fixed to steel with the galvanized steel loop wire or the twice plastic clip,
- is positioned at the intersection of the steels,
- Suitable for all steel diameters.

The application requires 4 to 6 spacer/m<sup>2</sup>.

### Characteristics

These concrete spacer are available in two qualities, the characteristics of which you will find below: Standard concrete and Q12 quality concrete.

|                                   | Standard concrete                                                                                                                |
|-----------------------------------|----------------------------------------------------------------------------------------------------------------------------------|
| <b>Material composition</b>       | <ul style="list-style-type: none"> <li>- Cement CEM I,</li> <li>- Sand 0-2,</li> <li>- Plasticizer,</li> <li>- Water.</li> </ul> |
| <b>Resistance Class</b>           | C50/60                                                                                                                           |
| <b>Compressive strength (MPa)</b> | > 50                                                                                                                             |
| <b>w/c</b>                        | 0,38                                                                                                                             |
| <b>Exposure class</b>             | XD1-XD3, XS1-XS3, XF1-XF4, XA1-XA2                                                                                               |

|                                   |                                                                                                                                                        |
|-----------------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------|
|                                   | <b>Q12 quality concrete</b>                                                                                                                            |
| <b>Material composition</b>       | <ul style="list-style-type: none"><li>- Cement CEM I SR3,</li><li>- Sand 0-2,</li><li>- Silica fume,</li><li>- Plasticizer,</li><li>- Water.</li></ul> |
| <b>Resistance Class</b>           | C50/60                                                                                                                                                 |
| <b>Compressive strength (MPa)</b> | > 50                                                                                                                                                   |
| <b>w/c</b>                        | 0,38                                                                                                                                                   |
| <b>Exposure class</b>             | XC1-XC4, XD1-XD3, XS1-XS3, XF1-XF4, XA1-XA3                                                                                                            |

The information provided in this document is for guidance only and reflects our current knowledge. We shall not be responsible or liable for any improper or inappropriate use of our products.

Given the wide range of possible uses, our recommendations do not exempt users from carrying out their own tests. Our laboratory and technical department will be happy to provide you with any information you may require.

TAM Groupe Z.I. Avenue Albert Einstein.  
CS 90043 - 77555 Moissy Cramayel Cedex - France  
S.A.S. au capital de 883 332 € RCS Melun B  
SIRET 313 659 674 00029 - FR 76 313 659 674

Tel. : + 33 1 64 13 30 00 – [tamgroupe@tamgroupe.fr](mailto:tamgroupe@tamgroupe.fr) – [www.tamgroupe.fr](http://www.tamgroupe.fr)