


TECHNICAL FEATURES

MODEL:	PORTLANDSTONE MARFIL
FORMAT:	120x120
THICKNESS(mm):	
DATE:	03/07/2025
CODE:	017.120.0033.14579
GROUP:	GRUPO B1a UNE-EN 14411 Anexo G / SASO GSO ISO 13006:2022 Anexo G
TILE TYPE:	GL
FINISH:	RECTIFIED MATT
FAMILY:	PORCELAIN TILES
NUMBER OF DESIGNS:	



TEST		RESULT
	UNE-EN ISO 10545-2	DIMENSIONAL FEATURES COMPLIES WITH THE STANDARD
	UNE-EN ISO 10545-3	WATER ABSORPTION <= 0,5 %
	UNE-EN ISO 10545-4	MODULUS OF RUPTURE - BREAKING STRENGTH 1600-2400 N
		MODULUS OF RUPTURE - BENDING STRENGTH 35-45 N/mm2
	UNE-EN ISO 10545-6	RESISTANCE TO DEEP ABRASION (MM3) <130 mm3
	UNE-EN ISO 10545-7	RESISTANCE TO SURFACE ABRASION -
	UNE-EN ISO 10545-8	LINEAR THERMAL EXPANSION <7,0 x 10-6 °C-1
	UNE-EN ISO 10545-9	THERMAL SHOCK RESISTANCE RESISTS
	UNE-EN ISO 10545-11	CRAZING RESISTANCE RESISTS
	UNE-EN ISO 10545-12	FROST RESISTANCE RESISTS
	UNE-EN ISO 10545-13	CHEMICAL RESISTANCE - AMMONIUM CHLORIDE 100 G/L A
		CHEMICAL RESISTANCE - SODIUM HYPOCHLORITE 20 MG/L A
		CHEMICAL RESISTANCE - HYDROCHLORIC ACID 3% COMPLIES WITH THE STANDARD
		CHEMICAL RESISTANCE - CITRIC ACID 100 G/L COMPLIES WITH THE STANDARD
		CHEMICAL RESISTANCE - POTASSIUM HYDROXYDE 30 G/L COMPLIES WITH THE STANDARD
	UNE-EN ISO 10545-14	STAIN RESISTANCE - GREEN AGENT IN LIGHT OIL 5
		STAIN RESISTANCE - IODINE SOLUTION IN ALCOHOL 5
		STAIN RESISTANCE - OLIVE OIL 5

TECHNICAL FEATURES

SLIP RESISTANCE

TEST		RESULT
	EN 16165:2022 Anexo C	SLIP RESISTANCE (PENDULUM)
		CLASE 1
	EN 16165:2022 Anexo A - Pie calzado	CRITICAL ANGLE OF SLIP (INCLINED PLATFORM)
		R9
	EN 16165:2022 Anexo A - Pie descalzo	CRITICAL ANGLE OF SLIP. WET-LOADED BAREFOOT AREAS
		-
BS7976 (PTV) WET	CLASSIFICATION ACCORDING TO PENDULUM TEST VALUES (PTV) WET	36+
EN 16165:2022 Anexo B	DYNAMIC COEFFICIENT OF FRICTION (DCOF) OF RIGID FLOORS.	-

TEST	VALOR UPEC
	UPEC CERTIFICATION
	-

Declaration of Performance:

https://www.pamesa.com/ERP/4.0/empresas/151/045/ficheros/t00030006/113/DdP_DoP_N003CPR2013.pdf